

PENNDOT AGGREGATE SPECIFICATION



NY (315) 437-1977 • PA (215) 692-0452 • sales@emeraldscreening.com

Total Percent Passing

AASHTO Number	100 mm (4")	90 mm (3 1/2")	63 mm (2 1/2")	50 mm (2")	37.5 mm (1 1/2")	25.0 mm (1")	19.0 mm (3/4")	12.5 mm (1/2")	9.5 mm (3/8")	4.75 mm (No. 4)	2.36 mm (No. 8)	1.18 mm (No. 16)	150 μm (No. 100)	75 μm (No. 200)
1	100	90-100	25-60		0-15		0-5							
3			100	90-100	35-70	0-15		0-5						
467				100	95-100		35-70		10-30	0-5				
5					100	90-100	20-55	0-10	0-5					
57					100	95-100		25-60		0-10	0-5			
67						100	90-100		20-55	0-10	0-5			
7							100	90-100	40-70	0-15	0-5			
8								100	85-100	10-30	0-10	0-5		
10									100	85-100			10-30	
2A**				100			52-100		36-70	24-50	16-38*	10-30		
OGS**				100			52-100		36-65	8-40		0-12		

*Applies only for bituminous mixtures

**PENNDOT Number

www.emeraldequipmentsystems.com

