
RECIPE - 9CL THE TEMPTRESS IN CS1



CANDLE SHACK

DESCRIPTION



INGREDIENTS FOR EACH CANDLE

 1x 9cl glass jar

 5.25g of The Temptress Fragrance Oil

 69.75g of Candle Shack CS1 Container Wax

 1x LX8 Wick

 1x 15mm Adhesive Wick Pad

 1x WickClaw Tool for 9cl Glass

WAX

Candle Shack's CS1 Container Wax is blended from mineral and rapeseed oil. It is optimised for scent throw and maintains excellent hot and cold throw while using less fragrance. This vegan-friendly container wax also has a beautiful white texture and unmatched stability, making it popular with our luxury clients.

VESSEL

Our Lauren 9cl Votive glass is manufactured in Italy and meets the highest standards of clarity and tolerance. Height: 67mm Diameter: 56mm Internal height: 57mm

WICK

The Wedo LX candle wick series is one of Wedo's simplest and most popular wicks. Suitable for paraffin container candles, votives and pillar candles, the LX wicks are made of cotton and are without cores. All wicks are 110mm long with a thin paraffin wax coating for stability.

USAGE RECOMMENDATIONS

- We recommend heating CS1 to 75°C to melt.
- Add the fragrance at 70°C and stir for 60 seconds.
- Warm your glasses by putting them in a 40° C oven for 5 to 10 minutes.
- The mixture is ready to pour at 65°C into warmed glasses.
- If the top is uneven once set, you can flash the surface with a heat gun or do a top-up pour to get a clean finish.
- Leave the candle to cure for at least 2 days for the best results.

DISCLAIMER

Each report shows test results for a set of candles made by Candle Shack's R&D team for that particular recipe. The test reports are not a guarantee that all candles made to the recipe will burn in exactly the same way. Variables such as ambient temperature, air flow, or the manufacturing process can affect the burning profile of a candle, so it is recommended that candle makers conduct their own testing to ensure that they are satisfied with the performance of their product.



Candleshack Ltd, Unit A, West Carron Works, Stenhouse Road, Carron, Stirlingshire, FK2 8DR

Technical report on a test set of candles made in Candle Shack R&D department for sooting behaviour testing and fire safety testing

Date of Report: 05/01/23

Testing Period: 13/12/2022 - 16/12/2022

Sample Ref	RCP0084F-2	No. of Samples	3			
Candle Name	9cl The Temptress Candle, 7% in CS1					
Description	75g Blened Mineral Wax Fragranced Candle					
Fragrance	The Temptress	Weight per candle	5.25g			
Wax	Candle Shack Blended Mineral CS1		Weight per candle	69.75g		
Colour	White	Height	67mm			
Wick Type	LX8	Top Diameter (ext)	56mm			
Wick Positioning	Centred	Top Diameter (int)	51mm			
Surface Defects	None	Base Diameter	50mm			

TECHNICAL REPORT

Part 1: SPECIFICATION FOR SOOTING BEHAVIOUR

To evaluate the performance of a test set of candles in a controlled environment against the requirements of **BS EN 15426:2018** (Candles. Specification for sooting behaviour)

Part 2: SPECIFICATION FOR FIRE SAFETY

To evaluate the performance of a test set of candles in a controlled environment against the requirements of **BS EN 15493:2019** (Candles. Specification for fire safety)



Part 1: SPECIFICATION FOR SOOTING BEHAVIOUR

Requirement

When tested in accordance with clause 9 of EN 15426:2018, the average soot index per hour from three tests (samples) shall be less than 1.0/h

The room temperature during testing was 20±5°C

Wicks were trimmed to 5mm before lighting. Cycles: 3 x 240 ± 5 min cycles with >60min pause between cycles) Soot testing was performed in wire mesh cylinder Type 2 (Diameter: 300 ± 10 mm)

Sample Ref.	Total burn time t_m (h)	Hourly soot index Si _h	Average soot index per hour Si _h	Result
RCP0084F-2.1	8.00	0.18		
RCP0084F-2.2	8.00	0.18	0.14	PASS
RCP0084F-2.3	8.00	0.06		

۲

Page 1 of 5

 \odot





Part 1: SPECIFICATION FOR SOOTING BEHAVIOUR

Requirement


When tested in accordance with clause 9 of EN 15426:2018, the average soot index per hour from three tests (samples) shall be less than 1.0/h


The room temperature during testing was 20±5°C Wicks were trimmed to 5mm before lighting.

Cycles: 3 x 240 ± 5 min cycles with >60min pause between cycles) Soot testing was performed in wire mesh cylinder Type 2 (Diameter: 300 ± 10 mm)

Sample Ref.	Total burn time $t_{\rm m}$ (h)	Hourly soot index Si _h	Average soot index per hour Si _h	Result
RCP0084F-2.1	8.00	0.18		
RCP0084F-2.2	8.00	0.18	0.14	PASS
RCP0084F-2.3	8.00	0.06		

CHARTS





 \odot

 \odot

Page 2 of 5

Page 4 of 5

