

RECIPE - 20CL PINK PEPPER & ROSE IN RCX

CANDLE SHACK

DESCRIPTION

PINK PEPPER AND ROSE

TOP NOTES - MANDARIN, BLACKCURRANT, PLUM, DAMSON HEART NOTES - CARNATION, LILY, ROSE, GERANIUM BASE NOTES - AMBER, SANDALWOOD, CEDARWOOD

INGREDIENTS FOR EACH CANDLE

1x 20cl glass jar 13.2g of Pink Pepper and Rose Fragrance Oil 151.8g of Candle Shack RCX Eco System Wax 1x CL10 Wick 1x 15mm Adhesive Wick Pad 1x WickClaw Tool for 20cl Glass

WAX

Candle Shack's EcoSystem Rapeseed & Coconut (RCX) is a natural wax blend. It was developed in Europe exclusively for Candle Shack and is made from rapeseed and coconut oil... and nothing else! It is free from paraffin, soy, palm, beeswax and synthetic additives.

VESSEL

Our Lotti 20cl glass is manufactured in Italy and meets the highest standards of clarity and tolerance. Height: 84mm Diameter: 70.5mm Internal height: 66mm

WICK

Our innovative unbleached cotton and linen blend CL10 wick. Flat wick designed to minimise afterglow and smoking while maintaining rigidity. All wicks are 110mm long with a thin paraffin wax coating for stability.

USAGE RECOMMENDATIONS

- We recommend heating RCX to 60°C to melt.
- Add fragrance at 60°C and stir for 60 seconds.
- The mixture is ready to pour at 38°C into slightly warmed glasses.
- If the top is uneven once set, you can flash the surface with a heat gun, or do a top up pour to get a clean finish.
- Leave the candle to cure for 2+ days for best results.

DISCLAIMER

Each report shows test results for a set of candles made by Candle Shack's R&D team for that particular recipe. The test reports are not a guarantee that all candles made to the recipe will burn in exactly the same way. Variables such as ambient temperature, air flow, or the manufacturing process can affect the burning profile of a candle, so it is recommended that candle makers conduct their own testing to ensure that they are satisfied with the performance of their product.



Candle Shack Ltd Unit A, West Carron Works Stenhouse Rd Carron Stirlingshire FK2 8DR

Technical report on a test set of candles made in Candle Shack R&D department for sooting behaviour testing and fire safety testing

Date of Report: 17/09/21

Testing Period: 01/09/21 to 08/09/21

Sample Ref	CS0268L	No. of Samples	3	
Candle Name	20cl Pink Pepper & Rose Petals, 8% in RCX			
Description	165g Rapeseed & Coconut Wax Fragranced Candle			
Fragrance	Pink Pepper & Rose Petals	Weight per candle	13.2g	
Wax	Candle Shack RCX Eco System Wax		Weight per candle	151.8g
Colour	White	Height	84mm	
Wick Type	CL10	Top Diameter (ext)	70mm	
Wick Positioning	Centred	Top Diameter (int)	65mm	
Surface Defects	None	Base Diameter	67mm	

TECHNICAL REPORT

Part 1: SPECIFICATION FOR SOOTING BEHAVIOUR

To evaluate the performance of a test set of candles in a controlled environment against the requirements of **BS EN 15426:2018** (Candles. Specification for sooting behaviour)

Part 2: SPECIFICATION FOR FIRE SAFETY

To evaluate the performance of a test set of candles in a controlled environment against the requirements of **BS EN 15493:2019** (Candles. Specification for fire safety)



Candle Shack Ltd Unit A, West Carron Works Stenhouse Rd Carron Stirlingshire FK2 8DR

Part 1: SPECIFICATION FOR SOOTING BEHAVIOUR

Requirement

When tested in accordance with clause 9 of EN 15426:2018, the average soot index per hour from three tests (samples) shall be less than 1.0/h

The room temperature during testing was $20\pm5^{\circ}$ C Wicks were trimmed to 5mm before lighting. Cycles: 2 x 240 ± 5 min cycles with >60min pause between cycles) Soot testing was performed in wire mesh cylinder Type 1 (Diameter: 230 ± 10 mm)

	Sample Ref.	Total burn time <i>t</i> _m (h)	Hourly soot index Si _h	Average soot index per hour Si _h	Result
[CS0268L-1	8.00	0.14		
-[CS0268L-2	8.00	0.23	0.17	PASS
[CS0268L-3	8.00	0.14		



Candle Shack Ltd Unit A, West Carron Works Stenhouse Rd Carron Stirlingshire FK2 8DR

Part 2: SPECIFICATION FOR FIRE SAFETY

Test Property	Test Method	Requirements	Result
Stability	tability EN 15493:2019 4.1 Candle should not tip over when placed (Visual Check) on a 10° incline plane		PASS
Secondary Ignition	EN 15493:2019 4.2 (Visual Check)	No secondary ignition shall occur for more than 10 s	PASS
Flame Height	EN 15493:2019 4.3 (Measurement)	The flame height for all candle types, except for tea lights, shall not exceed 75mm. The flame height for tea lights	PASS
	(shall not exceed 30mm	Maximum: 30 mm
	EN 15493:2019 4.5.1 (Visual Check)	After extinguishing the candle shall not spontaneously re-light	PASS
Behaviour after extinguishing	EN 15493:2019 4.5.2 (Measurement)	The wick shall not continue to glow or smoke for an average time of more than 30 s after extinguishing	PASS
			Average: 8 s
Container Candles	EN 15493:2019 4.6 (Visual Check)	The container shall not crack or break at any time throughout the burning test	PASS

The room temperature during testing was 20±5°C Wicks were trimmed to 5mm before lighting.

Candle Performance (240 ± 5 min cycles with >60min pause between cycles)

Sample Ref.	Gross Weight (g)	Total Wax Consumed (g)	*Total Burning Time (h)	Wax Consumption Rate (g/h)
CS0268L-1	416.2	161.0	37.5	4.29
CS0268L-2	409.1	149.7	33.5	4.47
CS0268L-3	414.9	154.8	37.5	4.13


*If a candle self-extinguishes during the final burn cycle, the time of self-extinguishing is estimated


Notes and Discussion:



Candle Shack Ltd Unit A, West Carron Works Stenhouse Rd Carron Stirlingshire FK2 8DR

CHARTS





Page 4 of 5

