

RECIPE - 9CL

SOLARIS BLANC IN 464 (NOW MADE IN EUROPE)

CANDLE

DESCRIPTION



INGREDIENTS FOR EACH CANDLE

1x 9cl Candle Jar

7.5g of Solaris Blanc Fragrance Oil

67.5g of Golden Wax 464 (Now made in Europe)

1x TCR15/08 Wick

1x 15mm Adhesive Wick Pad

1x Three Jar Wick Centering Tool

WAX

Made by global wax giant AAK in Sweden, Golden Wax 464 is an excellent soy container wax. It offers a powerful hot and cold scent throw, fantastic glass adhesion, smooth resets and is produced under rigorous ethical and environmental standards.

VESSEL

Our Lauren 9cl Votive glass is manufactured in Italy and meets the highest standards of clarity and tolerance.

Height: 67mm
Diameter: 56mm
Internal height: 57mm

WICK

RAL-accrediated TCR wicks are meticulously crafted by Monterosa from unbleached cotton, intricately interwoven with a delicate paper thread and encased in a protective outer jacket. To ensure optimal performance, the wicks are then expertly waxed and crimped by Candle Shack in Scotland.

USAGE RECOMMENDATIONS

- We recommend working at an ambient temperature of 18 to 25°C.
- We recommend heating 464 to 70°C to melt.
- Add the fragrance at 65-70°C and stir until homogeneous.
- The mixture is ready to pour at 60-70°C into jars at room temperature.
- If the top is uneven once set, you can flash the sur face with a heat gun.
- Leave the candle to cure for at least 2 days at 18 to 25°C for consistent results.

DISCLAIMER

Each report shows test results for a set of candles made by Candle Shack's R&D team for that particular recipe. The test reports are not a guarantee that all candles made to the recipe will burn in exactly the same way. Variables such as ambient temperature, air flow, or the manufacturing process can affect the burning profile of a candle, so it is recommended that candle makers conduct their own testing to ensure that they are satisfied with the performance of their product.



Candleshack Ltd, Unit A, West Carron Works, Stenhouse Road, Carron, Stirlingshire, FK2 8DR

Technical report on a test set of candles made in Candle Shack R&D department for sooting behaviour testing and fire safety testing

Date of Report: 22/03/24 Testing Period: 14/03/2024 - 20/03/2024

Sample Ref	RCP0138G-1	No. of Samples	3		
Candle Name	9cl Solaris Blanc Candle, 10% in EU464				
Description	75g Soy Wax Fragranced Candle				
Fragrance	Solaris Blanc		Weight per candle	7.5g	
Wax	GoldenWax 464 (now made in Europe)		Weight per candle	67.5g	
Colour	Off-White	Height	67mm		
Wick Type	TCR15/08	Top Diameter (ext)	56mm		
Wick Positioning	Centred	Top Diameter (int)	51mm		
Surface Defects	None	Base Diameter	50mm		

TECHNICAL REPORT

Part 1: SPECIFICATION FOR SOOTING BEHAVIOUR

To evaluate the performance of a test set of candles in a controlled environment against the requirements of BS EN 15426:2018 (Candles. Specification for sooting behaviour)

Part 2: SPECIFICATION FOR FIRE SAFETY

To evaluate the performance of a test set of candles in a controlled environment against the requirements of BS EN 15493:2019 (Candles. Specification for fire safety)



CANDLE SHACK

Part 1: SPECIFICATION FOR SOOTING BEHAVIOUR

Requirement

When tested in accordance with clause 9 of EN 15426:2018, the average soot index per hour from three tests (samples) shall be less than 1.0/h

The room temperature during testing was 20±5°C

Wicks were trimmed to 5mm before lighting.

Cycles: 2 x 240 ± 5 min cycles with >60min pause between cycles)

Soot testing was performed in wire mesh cylinder Type 1 (Diameter: 230 ± 10 mm)

Sample Ref.	Total burn time t_m (h)	Hourly soot index Si _h	Average soot index per hour Si _h	Result
RCP0138G-2.1	8.00	0.00		
RCP0138G-2.2	8.00	0.03	0.03	PASS
RCP0138G-2.3	8.00	0.07		



CANDLE SHACK

Part 2: SPECIFICATION FOR FIRE SAFETY

Test Property	Test Method	Test Requirements	Result	
Stability	EN 15493:2019 4.1	Candle should not tip over when placed on	PASS	
	(Visual Check)	a 10° incline plane	A 10000000000000	
Secondary Ignition	EN 15493:2019 4.2	No secondary ignition shall occur for more	PASS	
	(Visual Check)	than 10 s	17.00	
Flame Height		The flame height for all candle types,		
	EN 15493:2019 4.3	except for tea lights, shall not exceed	PASS	
	(Measurement)	75mm. The flame height for tea lights shall		
		not exceed 30mm	Maximum: 15 mm	
Behaviour after extinguishing	EN 15493:2019 4.5.1	After extinguishing the candle shall not	PASS	
	(Visual Check)	spontaneously re-light	PASS	
	EN 15493:2019 4.5.2 (Measurement)	The wick shall not continue to glow or smoke for an average time of more than	PASS	
	(30 s after extinguishing	Average: 5 s	
Container Candles	EN 15493:2019 4.6 (Visual Check)	The container shall not crack or break at any time throughout the burning test	PASS	

The room temperature during testing was 20±5°C

Wicks were trimmed to 5mm before lighting.

Candle Performance (240 ± 5 min cycles with >60min pause between cycles)

Sample Ref.	Gross Weight (g)	Total Wax Consumed (g)	*Total Burning Time (h)	Wax Consumption Rate (g/h)
RCP0138G-2.1	195.4	56.8	20.0	2.84
RCP0138G-2.2	196.1	57.3	20.0	2.87
RCP0138G-2.3	195.9	57.8	20.0	2.89

^{*}If a candle self-extinguishes during the final burn cycle, the time of self-extinguishing is estimated.


Notes and Discussion:




Page 3 of 5

CANDLE SHACK

CHARTS








CANDLE SHACK

IMAGE GALLERY



End of Burn Front - Sample 1



End of Burn Front - Sample 2



End of Burn Front - Sample 3



End of Burn Top - Sample 1



End of Burn Top - Sample 2



End of Burn Top - Sample 3

END OF REPORT

Tatryga Kajewska

Patrycja Krajewska

Development Technologist

