Remark: Our processor for is only for the most widely used materials. Customers may need to try other uncommon materials by themselves, or they can contact us to apply for testing.

Engraving Parameter for Common Material

Material	Engraving						
	Max Intensity	Speed (mm/s)	Max Power	Image Mode	Modify to be Mechanical	Number of passes	Item Illustration
Basswood	0.1	1200	40%	Floyd-Steinberg	N/A	1	
Yellow pine (soft wood)	0.1	1200	11%	Floyd-Steinberg	N/A	1	
Mahogany	0.1	1200	45%	Floyd-Steinberg	N/A	1	
Pine	0.1	1200	40%	Stucki	N/A	1	
Hardwoods (solid wood)	0.1	1200	45%	Floyd-Steinberg	N/A	1	
Bamboo	0.1	1200	50%	Floyd-Steinberg	N/A	1	
Leather	0.1	1200	45%	Floyd-Steinberg	N/A	1	
Acrylic	0.1	1200	40%	Floyd-Steinberg	N/A	1	ATOMSTACK
Stainless	0.1	1200	60%	Floyd-Steinberg	Yes	1	
Anodized Alu	0.1	1200	60%	Floyd-Steinberg	N/A	1	
stone tile	0.1	300	60%	Floyd-Steinberg	N/A	1	ATOMSTACK
Glass	0.1	1200	50%	Floyd-Steinberg	Yes	1	
Acrylic	0.1	1200	50%	Floyd-Steinberg	N/A	1	
Translucent Acrylic	0.1	1200	11%	Jarvis	N/A	1	
Iron color plate	0.1	1200	11%	Floyd-Steinberg	N/A	1	
Plastic	0.1	1200	45%	Floyd-Steinberg	N/A	1	
Resin	0.1	1200	11%	Floyd-Steinberg	N/A	1	
Artificial Stone	0.1	1200	50%	Floyd-Steinberg	N/A	1	
High density foam board	0.1	1200	11%	Floyd-Steinberg	N/A	1	
Rubber	0.1	1200	50%	Floyd-Steinberg	N/A	1	
Multi-Ply	0.1	1200	11%	Stucki	N/A	1	
Office paper	0.125	1200	11%	Floyd-Steinberg	N/A	1	
PP painting board	0.1	1200	11%	Floyd-Steinberg	N/A	1	
Leather	0.1	1200	11%	Floyd-Steinberg	N/A	1	
MDF	0.125	1200	20%	Stucki	N/A	1	
Mirror	0.08	1200	60%	Floyd-Steinberg	Yes	1	
Slate	0.1	1200	60%	Stucki	N/A	1	ATOMSTACK
Cardboard	0.1	1200	60%	Floyd-Steinberg	N/A	1	
Crystal Stone	0.1	1200	60%	Floyd-Steinberg	Yes	1	
PVC Board	0.1	1200	60%	Floyd-Steinberg	N/A	1	
Silver Stainless Steel	0.1	300	60%	Floyd-Steinberg	N/A	1	
Gunmetal Stainless Steel	0.08	1200	60%	Floyd-Steinberg	N/A	1	
Galvanized Iron	0.1	120	60%	Floyd-Steinberg	Yes	1	
Iron sheet	0.1	120	60%	Floyd-Steinberg	Yes	1	
Artificial acrylic	0.1	50	60%	Floyd-Steinberg	N/A	1	LOVE

Cutting Parameter for Common Material

Material	Cutting				
	Thickness	Speed (mm/s)	C.Max	Number of passes	Item Illustration
Basswood	3mm(in)	100	70%	2	
	6mm(in)	100	100%	3	
Pine	3mm(in)	100	80%	2	
	6mm(in)	100	100%	3	
Hardwoods (solid wood)	3mm(in)	100	70%	2	
	5mm(in)	100	100%	3	
Yellow pine (soft wood)	3mm(in)	1000	70%	2	
	5mm(in)	100	100%	3	
Bamboo	3mm(in)	100	100%	2	
	5mm(in)	100	100%	3	
Leather	2mm(in)	100	80%	2	
Multi-Ply	3.2mm(in)	100	80%	2	
Acrylic	3mm(in)	100	60%	2	
	5mm(in)	100	100%	3	
MDF	3mm(in)	100	100%	2	
	5mm(in)	100	100%	3	
Stainless Steel Sheet	0.08mm(in)	100	60%	2	