RUST CONVERTER ULTRA instantly bonds with rust, stops its growth, transforms it into a non-rusting, paintable surface, and prevents future rust formation.

DIRECTIONS:

SURFACE PREPARATION: Remove large rust and scale particles with a wire brush or sandpaper. Clean the surface thoroughly to remove dirt, dust and grease.

APPLICATIONS: Mix / shake thoroughly before using. This product is ready-to-use. Do not dilute. Do not apply this product if the surface temperatures are below 50°F.

BRUSH: For maximum penetration, work product into the rusted surface with a synthetic bristle brush. On large areas use a roller or airless sprayer. Apply a second coat 20-30 minutes later in a cross direction to previous coat. Allow to dry for 48 hours before painting.

SPRAYER: Spray with an airless sprayer with 0.11-0.13 tip at 800-1200 psi. Adjust pressure as needed. One gallon covers 200-300 sq ft on a smooth, non-porous surface.

DRYING TIME: The resulting coat will dry to a smooth, dark finish in 20-30 minutes. Apply a second coat to ensure complete transformation of rusty surfaces. Allow 48 hours of cure time before the application of the finished paint coat. For long-lasting protection of iron surfaces, the cured rust converter should be sealed with two coats of a high quality oil-based paint. No other primer is required.

IMPORTANT: Do NOT return unused material to original container.

CLEAN-UP: Application equipment should be cleaned immediately with soap and water.



KEEP OUT OF REACH OF CHILDREN

Offer Empty container for recycling. If recycling is not available dispose of container in the trash.

⚠ WARNING: This product can expose you to Vinylidene chloride (1,1-Dichloroethylene), which is known to the State of California to cause cancer, and Ethylene glycol (ingested) which is known to the State of California to cause birth defects or other reproductive harm. For more information go to www.P65Warnings.ca.gov.

NFPA® Ratings

Health: 1; Flammability: 0; Reactivity: 0

Contains/CAS Number:

Water/7732-18-5; Butoxyethanol/111-76-2; Tannic Acid/1401-55-4; Propylene Glycol/57-55-6; Oxalic Acid Dihydrate/6153-56-6; Vinylidene Chloride/75-35-4; Ethylene Glycol/107-21-1

DISTRIBUTED BY:

Citywide Direct Carle Place, NY 11514 citywidedirect.com 888-839-5861



RECYCLE PLEASE