



# Aquaproof 202

Two Part Cementitious Waterproofing Membrane

## Features

- ▶ Two Part
- ▶ Cementitious
- ▶ Fast Curing
- ▶ Flexible
- ▶ Excellent Adhesion
- ▶ Non Toxic
- ▶ Easy to Apply
- ▶ Water Clean-up
- ▶ AS4858 Compliant
- ▶ No Solvent
- ▶ UV Stable

[www.pasco.net.au](http://www.pasco.net.au)

### Product Description

**Aquaproof 202** is a two-part liquid applied cementitious waterproofing membrane with fibre reinforcement. When applied and fully cured it forms a tough, flexible and seamless waterproofing membrane which exhibits excellent adhesion to most building substrates such as: concrete, render, concrete blocks, cement sheet, plaster board etc.

**Aquaproof 202** is UV stable and suitable for light pedestrian traffic. It can also be used for detailing of parapets and flashings.

### Features & Benefits

- Two-part
- Fast curing
- Excellent adhesion
- Low odour
- Flexible
- Non-toxic
- Complies to AS4858
- Trafficable (pedestrian traffic)

### Uses

- Under tiles in bathrooms
- Shower recesses
- Roof tops
- Laundries
- Balconies and Decks

### Waterproofing Standards

**Aquaproof 202** has been tested and approved in accordance to:  
• AS4858:2004 "Wet Area Membranes"

### Preparation

- All surfaces must be structurally sound and free of dirt, dust, grease, paint, oil, form release, curing agents and other contaminants.
- All protrusions are to be removed and all voids, cracks, joints etc. filled prior to membrane application (refer to application).
- Ensure substrate has adequate falls i.e. 1:80 for wet areas and 1:100 for balconies and decks.



# Aquaproof 202

Two Part Cementitious Waterproofing Membrane

## Application

- Prime all surfaces using **Aquaprime WB** or **Aquaprime SB Primer** and allow to dry. For external applications, prime area to be waterproofed with **Aquaprime WBE Primer**. All metal and PVC surfaces are to be primed with an etching primer.
- Cracks greater than 2mm are to be routed out and filled with **PascoFlex PU25**.
- Movement joints are to be filled with **PascoFlex PU25** with a 50mm bond breaker tape over the joint\* or reinforcement fabric embedded in **Aquaproof 202**.
- All sheet flooring is to be installed as per manufactures application instructions. Apply 140mm reinforcing fabric embedded in **Aquaproof 202** to all sheet flooring joints.
- Seal perimeter of taps and shower roses with **PascoFlex PU25** or **Hypersil GP**.\*
- Apply a 10-12mm bead of **PascoFlex PU25** or **Hypersil GP** to all internal horizontal and vertical corners, tool to a smooth concave shape and allow to cure.
- At all internal corners and penetrations apply a 140mm wide reinforcing fabric embedded in **Aquaproof 202**.
- Mixing: Add 10kg powder into 20L Pail. Mix contents using low speed mixing drill and allow to stand for 5 minutes. Add remaining 10kg powder and mix until smooth creamy consistency.
- Apply the first coat of **Aquaproof 202** to the entire area that needs to be waterproofed, using a roller or brush and allow to dry.
- Apply the second coat of **Aquaproof 202** to the same area at a 90° angle to the first coat ensuring no pinholes or bubbles. Recoat if necessary and allow to cure.
- Do not apply heavy coats of **Aquaproof 202** in corners as shrinkage cracks may occur.

\*Allow sealant to cure prior to membrane application.

## Precautions

- Do not apply if temperature is above 35°C or less than 8°C.
- Ensure product is fully cured prior to tiling.
- Do not apply if rain is imminent.
- Walls in shower recesses are to be coated just above the shower rose.
- Ensure sheet flooring is appropriately fixed as per manufacturers' instructions.
- In external applications consider a slip sheet between membrane and toppings greater than 50mm and allow adequate expansion joints.
- **Aquaproof 202** is not suitable for heavy traffic.

## Coverage

- 1.7Lt per m<sup>2</sup> (2 coats).
- Dry film thickness of approximately 1.2mm.

## Clean Up

Tools and excess product can be cleaned with water, while still wet. Cured material may be removed by mechanical means and the use of **Pasco Xylene**.

## Packaging

**Aquaproof 202**: 20Kg Powder + 20 Liquid Copolymer.

## Colour

**Aquaproof 202** is available in Grey.

## Shelf Life

6 months minimum, when stored in cool, dry conditions below 25°C.



241 Ingles Street  
Port Melbourne, VIC 3207  
Ph: (03) 9429 9111

4/14 Tennyson Road  
Gladesville, NSW 2111  
Ph: (02) 9817 4441



# Aquaproof 202

Two Part Cementitious Waterproofing Membrane

## Health and Safety

Keep out of reach of children. Wear suitable protective clothing, gloves and eye/face protection. Uncured sealant may cause skin, eye and respiratory system irritation. Use only in well ventilated areas.

In case of contact with eyes, rinse immediately with plenty of water and contact a Doctor or Poisons Information Centre (Ph 13 11 26). In case of skin contact, wash affected area with hand cleaner followed by soap and water.

Material Safety Data Sheets must be read and understood prior to using **Aquaproof 202**.

Technical Specifications	
Property	Result
Viscosity	Liquid
Tack Free Time	3 hours @ 0.6mm DFT
Full Cure @ 25°C	24 hours
Floor coverage	1.7 litres/m <sup>2</sup>
Floor Dry film thickness	1.2mm
Solids Content	70%
Pot Life	Use within 5 hours
Application surface temp.	10-35
Elongation at break	>180%

*Pasco Construction Solutions Pty Ltd offers its' products for sale, subject to its standard terms and conditions of sale, which are available upon request. All endeavors have been made to ensure the information provided in this technical data sheet is accurate and correct, however as the use of this material is beyond the supplier's control, liability is limited to replacement of material proven faulty. It is the responsibility of the purchaser to ensure that the product is suitable for the specific application and that it is applied in accordance with the supplier's recommendations.*



241 Ingles Street  
Port Melbourne, VIC 3207  
Ph: (03) 9429 9111

4/14 Tennyson Road  
Gladesville, NSW 2111  
Ph: (02) 9817 4441