



## StormBreaker™ Acrylic Base Coat

### PRODUCT DESCRIPTION:

**STORMBREAKER™ ACRYLIC BASE COAT** is a high solids, technologically advanced, fire retardant, thixotropic, 100% acrylic elastomeric uniquely formulated for the protection of spray polyurethane foam, metal, and with roofing fabric over a variety of other roof substrates. The proprietary formulation incorporates high solids elastomeric acrylic resins, reinforcing laminar pigments and non-migrating fire retardants to produce a seamless, flexible, durable membrane having exceptional weatherability, ultraviolet and fire resistance. **STORMBREAKER™ ACRYLIC BASE COAT** acts as a “breathing” membrane allowing trapped moisture vapor to pass through the film while remaining impervious to exterior mass water penetration.

### RECOMMENDED USES:

**STORMBREAKER™ ACRYLIC BASE COAT** is the ideal choice for metal roofs and spray polyurethane foam. This product also carries the **FM Global Approval (ASTM E108)** and **FM Severe Hail Rating**. The thixotropic nature of **STORMBREAKER™ ACRYLIC BASE COAT** permits high build coverage, even on rough, textured or vertical surfaces without pin holing or sagging. It also has excellent adhesion to metal and SPF. As with any acrylic coating, **ponding water conditions are to be avoided**. Please contact our Technical Service Department for primer recommendations for application over rusted surfaces.

### GENERAL APPLICATION INSTRUCTIONS:

**STORMBREAKER™ ACRYLIC BASE COAT** may be applied by heavy nap rollers, brushes or airless spray equipment. Airless spray is the most efficient application method for larger projects. Brushes and rollers may be used for detail work such as edge termination, filling of voids, pinholes and small cracks.

Apply **STORMBREAKER™ ACRYLIC BASE COAT** only to clean and dry sound substrates free of loose particles or other foreign matter. **STORMBREAKER™ ACRYLIC PRIMER** may be required subject to type of substrate to maximize adhesion and/or lock in rust. Contact our Technical Service Personnel for project specific primer recommendations and substrate preparation. **SOME SEPARATION MAY OCCUR DURING SHIPMENT AND STORAGE. THEREFORE, THE CONTENTS OF EACH CONTAINER SHOULD BE THOROUGHLY POWER MIXED FOR THREE (3) TO FIVE (5) MINUTES. DO NOT THIN PRODUCT.** It is recommended that all elastomeric coatings be sprayed in multiple coats applied in multidirectional passes (north-south/east-west) to insure uniform film build and to avoid pinholing. Backrolling sprayed material may be necessary to fill pinholes in substrate. Final dry film thickness (DFT) of the StormBreaker™ acrylic system over any substrate is to be a minimum of **25 dry mils** and free of voids, pin holes, holidays, cracks or blisters. **COATING APPLICATION SHOULD BE SUSPENDED IMMEDIATELY AND OUR TECHNICAL SERVICE PERSONNEL CONTACTED IF THE RESULTS BEING OBTAINED ARE LESS THAN DESIRABLE.**

### TYPICAL PHYSICAL PROPERTIES

#### WEIGHT PER GALLON:

11.4 lbs per gallon ± 0.2

**SHELF LIFE:** 12 months @ 45°- 80° F

**COLOR:** White, Gray or as specified

**VISCOSITY:** 8000 ± 1500 cP

**ELONGATION:** 315% ASTM D412

**RECOVERY:** 100% ASTM D412 **IMPACT RESISTANCE:**

Exceeds 160b in/lb. ASTM D-2294

**HARDNESS:** 45 Shore A ASTM D-2240

#### TENSILE STRENGTH:

400 psi; 3600 psi w/ fabric

ASTM D-412

#### PERMEABILITY:

3.4 perms ASTM E-96

#### ALGAE RESISTANCE:

No growth supported ASTM G29-96

#### FUNGI RESISTANCE:

No growth supported ASTM G29-96

#### SALT SPRAY:

No effect (3000 hours) ASTM B-117

#### WEATHERABILITY:

No effect (3800 hours) ASTM G-26

#### SERVICE TEMPERATURE:

-40° TO 200° F

**FIRE RATING:** FM Global Approved

#### HAIL RATING:

FM Severe Hail Rating FM Class

#### CURE TIMES:

**DRY TO TOUCH:** 4 Hours @ 75° F

**TACK FREE:** 12 Hours

**RECOAT:** 12-24 Hours

**SOLAR REFLECTANCE:** .82

**THERMAL EMITTANCE:** .90

**CRRCListed, EPA Energy Star Approved**

**Miami-Dade and Florida Building Code Approved**



# TECHNICAL DATA SHEET

3812 E 91<sup>st</sup> St, Cleveland, OH 44105 • (800) 350-2142 • [www.vikingpg.com](http://www.vikingpg.com)

Apply two (2) or more coats of **STORMBREAKER™ ACRYLIC BASE COAT** at the rate of 1-2 gallons per 100 square feet. As a visual aid in the application of the product, **STORMBREAKER™ ACRYLIC BASE COAT** gray may be used for the base coat. Darker colors are available and may accelerate the curing process in cooler ambient temperatures. Accentuated surface profiles that increase total surface area will require a proportionate increase in the amount of **STORMBREAKER™ ACRYLIC BASE COAT** to satisfy the minimum dry mil thickness specification requirements. No foot traffic should be permitted on the coated surface for 72 hours after application.

## GENERAL APPLICATION INSTRUCTIONS OVER METAL:

**STORMBREAKER™ ACRYLIC BASE COAT** may be applied to all types of metal substrates, including surfaces previously coated with similar acrylic coatings. Apply **STORMBREAKER™ ACRYLIC BASE COAT** only to clean, dry, sound surfaces free of loose particles or other foreign matter. Surface should be thoroughly inspected for oxidation. Conditions of all seams, fasteners and flashing areas should be checked for gaps, pinholes or cracks. Pressure washing is required as the initial step in the preparation of the substrate. All seams are to be sealed, fastener heads addressed and all roof penetrations inspected as well for possible water penetration. Strict adherence to the published consultant/architect specification is required. Viking Products Group, Inc., is not responsible for building engineering or structural design issues, internal or external. Please consult a building professional if such issues are suspected of having an affect on any roof restoration process.

## LIMITATIONS AND PRECAUTIONS:

**STORMBREAKER™ ACRYLIC BASE COAT** is a water based elastomeric acrylic coating that will freeze and become unusable at temperatures below 32° F. PROTECT FROM FREEZING DURING SHIPMENT AND STORAGE. Do not store material at temperatures below 45° F. Do not apply when ambient air and substrate temperatures fall below 50° F or when there is a possibility of temperatures dropping below 32° F within a 24 hour period after application. Do not apply over wet substrates or in inclement weather. Total cure of **STORMBREAKER™ ACRYLIC BASE COAT** requires complete evaporation of water. Cool temperatures and high humidity retard cure. Coatings can cause a premature artificial dew zone during the cure process under certain climatic conditions. This is generated as the water in the coating evaporated, cooling the surface and attracting moisture in the form of dew. Therefore, it is imperative not to apply the product if climatic conditions prevent complete cure before rain, dew or freezing temperatures. **STORMBREAKER™ ACRYLIC BASE COAT** is not a vapor barrier coating and is not recommended for use over cold storage installations. Where a vapor barrier is required, contact our Technical Service Personnel for proper selection and installation procedures. Use of acrylic coatings in darker colors over metal substrates may result in blistering if applied at coverage rates listed herein. Please contact our Technical Service Department for instructions for color coating installation.