



# TECHNICAL DATA SHEET

3812 E 91<sup>st</sup> St, Cleveland, OH 44105 • (800) 350-2142 • www.vikingpg.com



## SEBS Surface Filler

**StormBreaker™ SEBS Surface Filler** is a heavy rubber base/filler coat for various roofing substrates, including BUR and Modified Bitumen. It is an economical, one component product that is easy to use. STORMBREAKER™ SEBS SURFACE FILLER seals minor alligating and other surface irregularities, providing an excellent base for the RC 2000 and other StormBreaker Top-Coats to be applied.

**STORMBREAKER™ SEBS SURFACE FILLER** is a non-weatherable material. To achieve satisfactory weatherability, it must be coated with StormBreaker™ SEBS Coating.

### **SURFACE PREPARATION:**

The surface must be free of any moisture, rust scale, soil or other contaminants that may interfere with good adhesion. Remove any loose material from seams or other surfaces with a wire brush or scraper. Oil and grease should also be removed. In many cases high pressure water blast will be sufficient to prepare the surface.

### **APPLICATION TEMPERATURES:**

For best results, the temperature of the ambient air and the substrate should be within a range of 50°-100°F. For best spray application, the product should be at a minimum of 70°F. Lower temperatures can be utilized for brush applications.

### **APPLICATION METHODS:**

STORMBREAKER™ SEBS SURFACE FILLER can be applied by brush, spray or roller. Best results can be obtained with airless spray equipment. Contact Viking Technical Service for additional information.

### **Recommended Spray Equipment = Airless**

Tip size ..... 035"  
Fluid Pressure (PSI) ..... 3000 min.  
Fluid hose size..... 3/8" - 1/2"

### **TECHNICAL DATA:**

Coverage Rate..... 60-70 sf/gal  
Flashpoint ..... 101°F.  
Weight (lb./gal.)..... 9.2  
Solids (% by Weight) ..... 64.0 ±1%  
Viscosity @ 100°F ..... 5200 cps.  
Drying Time..... 2-4 hours  
Elongation..... 400%

### **HANDLING & STORAGE:**

StormBreaker™ SEBS Surface Filler contains a blend of solvents which is considered combustible by D.O.T. and O.S.H.A. standards. It should be used and stored away from flames, in a well-ventilated atmosphere. Avoid prolonged breathing of vapors and prevent contact with eyes. Read all label information and precautions before using.

The specifications, properties and performance of materials described herein are based on information believed to be reliable. Unless otherwise expressly provided in written contract, the products discussed are sold without conditions or warranties, expressed or implied. Product specifications are subject to change without notice.

Revision:09/2021