


**RECIPE - 9CL** 

# ROCK SALT AND DRIFTWOOD IN 464 (NOW MADE IN EUROPE)

WWW.CANDLE-SHACK.COM

# CANDLE

# **DESCRIPTION**



# **INGREDIENTS FOR EACH CANDLE**

1x 9cl Candle Jar

7.5g of Rock Salt And Driftwood Fragrance Oil

67.5g of Golden Wax 464 (Now made in Europe)

1x CL6 Wick

1x 15mm Adhesive Wick Pad

1x Three Jar Wick Centering Tool

## WAX

Made by global wax giant AAK in Sweden, Golden Wax 464 is an excellent soy container wax. It offers a powerful hot and cold scent throw, fantastic glass adhesion, smooth resets and is produced under rigorous ethical and environmental standards.

# **VESSEL**

Our Lauren 9cl Votive glass is manufactured in Italy and meets the highest standards of clarity and tolerance.

Height: 67mm Diameter: 56mm

Internal height: 57mm

# **WICK**

Crafted from unbleached cotton and interwoven with a linen thread, CL candle wicks are innovative flat wicks designed to minimise afterglow and smoking while maintaining rigidity. All wicks are 110mm long with a thin paraffin coating for stability.

# **USAGE RECOMMENDATIONS**

- We recommend working at an ambient temperature of 18 to 25°C.
- We recommend heating 464 to 70°C to melt.
- Add the fragrance at 65-70°C and stir until homogeneous.
- The mixture is ready to pour at 60-70°C into jars at room temperature.
- If the top is uneven once set, you can flash the sur face with a heat gun.
- Leave the candle to cure for at least 2 days at 18 to 25°C for consistent results.

# **DISCLAIMER**

Each report shows test results for a set of candles made by Candle Shack's R&D team for that particular recipe. The test reports are not a guarantee that all candles made to the recipe will burn in exactly the same way. Variables such as ambient temperature, air flow, or the manufacturing process can affect the burning profile of a candle, so it is recommended that candle makers conduct their own testing to ensure that they are satisfied with the performance of their product.



Candleshack Ltd, Unit A, West Carron Works, Stenhouse Road, Carron, Stirlingshire, FK2 8DR

Technical report on a test set of candles made in Candle Shack R&D department for sooting behaviour testing and fire safety testing

Date of Report: 14/02/24 Testing Period: 08/02/2024 - 12/02/2024

Sample Ref	RCP0035F-2	No. of Samples	3		
Candle Name	9cl Rock Salt & Driftwood Candle, 10% in EU464				
Description	75g Rapeseed & Coconut Wax Fragranced Candle				
Fragrance	Rock Salt & Driftwood		Weight per candle	7.5g	
Wax	GoldenWax 464 (now made in Europe)		Weight per candle	67.5g	
Colour	Off-White	Height	67mm		
Wick Type	CL6	Top Diameter (ext)	56mm		
Wick Positioning	Centred	Top Diameter (int)	51mm		
Surface Defects	None	Base Diameter	50mm		

#### **TECHNICAL REPORT**

#### Part 1: SPECIFICATION FOR SOOTING BEHAVIOUR

To evaluate the performance of a test set of candles in a controlled environment against the requirements of BS EN 15426:2018 (Candles. Specification for sooting behaviour)

#### Part 2: SPECIFICATION FOR FIRE SAFETY

To evaluate the performance of a test set of candles in a controlled environment against the requirements of BS EN 15493:2019 (Candles, Specification for fire safety)



#### Part 1: SPECIFICATION FOR SOOTING BEHAVIOUR

#### Requirement

When tested in accordance with clause 9 of EN 15426:2018, the average soot index per hour from three tests (samples) shall be less than 1.0/h

The room temperature during testing was 20±5°C

Wicks were trimmed to 5mm before lighting.

Cycles: 2 x 240 ± 5 min cycles with >60min pause between cycles)

Soot testing was performed in wire mesh cylinder Type 1 (Diameter: 230 ± 10 mm)

Sample Ref.	Total burn time $t_{\rm m}$ (h)	Hourly soot index Si <sub>h</sub>	Average soot index per hour Si <sub>h</sub>	Result
RCP0035F-2.1	8.00	0.07		
RCP0035F-2.2	8.00	0.13	0.10	PASS
RCP0035F-2.3	8.00	0.10		





# CANDLE SHACK

#### Part 2: SPECIFICATION FOR FIRE SAFETY

Test Property	Test Method	Test Requirements	Result
Stability	EN 15493:2019 4.1 (Visual Check)	Candle should not tip over when placed on a 10° incline plane	PASS
Secondary Ignition	EN 15493:2019 4.2 (Visual Check)	No secondary ignition shall occur for more than 10 s	PASS
Flame Height	EN 15493:2019 4.3 (Measurement)	The flame height for all candle types, except for tea lights, shall not exceed 75mm. The flame height for tea lights shall	PASS
		not exceed 30mm	Maximum: 15 mm
	EN 15493:2019 4.5.1 (Visual Check)	After extinguishing the candle shall not spontaneously re-light	PASS
Behaviour after extinguishing	EN 15493:2019 4.5.2 (Measurement)	The wick shall not continue to glow or smoke for an average time of more than	
	,	30 s after extinguishing	Average: 5 s
Container Candles	EN 15493:2019 4.6 (Visual Check)	The container shall not crack or break at any time throughout the burning test	PASS

The room temperature during testing was 20±5°C Wicks were trimmed to 5mm before lighting.

Candle Performance (240 ± 5 min cycles with >60min pause between cycles)

Sample Ref.	Gross Weight (g)	Total Wax Consumed (g)	*Total Burning Time (h)	Wax Consumption Rate (g/h)
RCP0035F-2.1	194.7	65.9	20.0	3.30
RCP0035F-2.2	198.5	70.4	24.0	2.93
RCP0035F-2.3	194.9	67.8	20.0	3.39

<sup>\*</sup>If a candle self-extinguishes during the final burn cycle, the time of self-extinguishing is estimated.


#### Notes and Discussion:




# Page 3 of 5

# CANDLE SHACK

#### **CHARTS**







# CANDLE SHACK

#### **IMAGE GALLERY**



End of Burn Front - Sample 1



End of Burn Front - Sample 2



End of Burn Front - Sample 3



End of Burn Top - Sample 1



End of Burn Top - Sample 2



End of Burn Top - Sample 3

## **END OF REPORT**

Patryga Krajewska

Patrycja Krajewska Development Technologist