TECHNICAL SPECIFICATION





JLT-602

Mono-Directional Filament Tape

Physical Properties Standard Metric Test Method Reinforcement Fiberglass Adhesive Synthetic Rubber PFT Backing Color Clear Total Thickness 0.10 mm ASTM D-3652 GB/T7125 3.9 mils Peel Adhesion 90° 83 oz/in 23N/25mm ASTM D-3330 GB/T2792 Holding Power ≥36 h ≥36 h ASTM D-3654 GB/T4851 Tensile strength 124 lbs/in 550N/25mm ASTM D-3759 GB/T7753 Elongation at Break 3-5% 3-5% ASTM D-3759 GB/T7753 Service Tem.--Mini **23**°F **-5**℃ BC/BD-220SE BC/BD-220SE Service Tem.--Max **158**°F **70°**℃ DHG-9055A DHG-9055A









Description:

JLT-602 Backed with PET film and reinforced with glass fiber. It's reinforced and economic mono-directional filament tape; suitable for intermediatestrength packing; bundling and box-sealing during the transportation; express-bag tear tape and pipe strapping.

Performance Features:

JLT-602 is a transparent and high strength filament tape. Glass fiber contributes higher tensile strength and improved synthetic rubber delivers stronger adhesion; high resistance to abrasion; impact resistance and high holding power.

Storage Condition:

It's recommended to store in clean and dry place. Damaged packaging shall be prevented. Not stored with volatile solvent. The temperature of storage shall be 4°C to 26°C and the humidity shall be between 40% and 50%. Rotate inventory recommended.

Shelf Life:

1 years from the date of shipment

The above properties and results obtained refer to the average values of laboratory testing carried out on the samples of Kingnode product. Kingnode does not guarantee testing accuracy and makes no guarantee of product performance, safety, or suitability, either expressed or implied, when used alone or in combination with other products. Kingnode strongly urges users to undertake independent testing in order to verify the suitability of the product for whatever intended use. Kingnode assumes no responsibility for any damage or injury sustained as a result of the use of its products.

Kingnode America Inc.

3005 Breckinridge Blvd suite 200, Duluth, GA 30096. United States Tel:+1 888-998-6866 info@kingnodetech.com https://kingnodetech.com