


TECHNICAL SPECIFICATION



JLT-605

Mono-Directional Filament Tape

Physical Properties	Standard	Metric	Test Method	
Reinforcement	Fiberglass			
Adhesive	Synthetic Rubber			
Backing	ВОРР			
Color	Clear			
Total Thickness	5.1 mils	0.13 mm	ASTM D-3652	GB/T7125
Peel Adhesion 90°	83 oz/in	23N/25mm	ASTM D-3330	GB/T2792
Holding Power	≥48 h	≥48 h	ASTM D-3654	GB/T4851
Tensile strength	124 lbs/in	550N/25mm	ASTM D-3759	GB/T7753
Elongation at Break	3-5%	3-5%	ASTM D-3759	GB/T7753
Service TemMini	23 °F	-5℃	BC/BD-220SE	BC/BD-220SE
Service TemMax	158°F	70℃	DHG-9055A	DHG-9055A













Description:

JLT-605 backed with BOPP film and reinforced with glass fiber. It's reinforced mono-directional filament tape; suitable for bundling heavy objects; pipe strapping; pallet fixing; reinforced marine carton packaging; good adhesion and holding power.

Performance Features:

JLT-605 is a transparent and reinforced filament tape. Glass fiber contributes higher tensile strength and improved synthetic rubber adhesive delivers stronger adhesion; high resistance to abrasion; impact resistance and high holding power.

Storage Condition:

Shelf Life:

1 years from the date of shipment

The above properties and results obtained refer to the average values of laboratory testing carried out on the samples of Kingnode product. Kingnode does not guarantee testing accuracy and makes no guarantee of product performance, safety, or suitability, either expressed or implied, when used alone or in combination with other products. Kingnode strongly urges users to undertake independent testing in order to verify the suitability of the product for whatever intended use. Kingnode assumes no responsibility for any damage or injury sustained as a result of the use of its products.

Kingnode America Inc.

3005 Breckinridge Blvd suite 200, Duluth, GA 30096. United States

Tel:+1 888-998-6866
info@kingnodetech.com
https://kingnodetech.com