



JLT-619

Mono-Directional Filament Tape

Physical Properties	Standard	Metric	Test Method	
Reinforcement	Fiberglass			
Adhesive	Synthetic Rubber			
Backing	PET			
Color	Clear			
Total Thickness	6.5 mils	0.165 mm	ASTM D-3652	GB/T7125
Peel Adhesion 90°	65 oz/in	18 N/25mm	ASTM D-3330	GB/T2792
Holding Power	≥48 h	≥48 h	ASTM D-3654	GB/T4851
Tensile strength	169 lbs/in	750 N/25mm	ASTM D-3759	GB/T7753
Elongation at Break	3-5%	3-5%	ASTM D-3759	GB/T7753
Service TemMini	23°F	-5℃	BC/BD-220SE	BC/BD-220SE
Service TemMax	158°F	70℃	DHG-9055A	DHG-9055A













Description:

JLT-619 Backed with PET film and reinforced with glass fiber. It's high strength mono-directional filament tape with good softness; special adhesive left no residue after peeled off; suitable for fixing the moving parts of refrigerator, air conditioner, household electrical appliances and other industries.

Performance Features:

JLT-619 is a transparent and high strength filament tape. Glass fiber contributes higher tensile strength and improved synthetic rubber delivers stronger adhesion; high resistance to abrasion; impact resistance and high holding power.

Storage Condition:

Shelf Life:

1 years from the date of shipment

The above properties and results obtained refer to the average values of laboratory testing carried out on the samples of Kingnode product. Kingnode does not guarantee testing accuracy and makes no guarantee of product performance, safety, or suitability, either expressed or implied, when used alone or in combination with other products. Kingnode strongly urges users to undertake independent testing in order to verify the suitability of the product for whatever intended use. Kingnode assumes no responsibility for any damage or injury sustained as a result of the use of its products.

Kingnode America Inc.

3005 Breckinridge Blvd suite 200, Duluth, GA 30096. United States

Tel:+1 888-998-6866
info@kingnodetech.com
https://kingnodetech.com