



## JLW-6614A

### Mono-Directional Clean Removal Filament Tape

Physical Properties	Standard	Metric	Test Method	
Reinforcement	Chemical Fiber			
Adhesive	Acrylic Pressure-Sensitive Adhesive			
Backing	PET			
Color	Clear			
Total Thickness	7.1 mils	0.18 mm	ASTM D-3652	GB/T7125
Peel Adhesion 90°	47 oz/in	13 N/25mm	ASTM D-3330	GB/T2792
Holding Power	≥48 h	≥48 h	ASTM D-3654	GB/T4851
Tensile strength	202 lbs/in	900 N/25mm	ASTM D-3759	GB/T7753
Elongation at Break	28-30%	28-30%	ASTM D-3759	GB/T7753
Service Tem.--Mini	14°F	-10°C	BC/BD-220SE	BC/BD-220SE
Service Tem.--Max	212°F	100°C	DHG-9055A	DHG-9055A

## TECHNICAL SPECIFICATION

### DESCRIPTION :

JLT-6614A Backed with PET film and reinforced with chemical fiber. It's high strength mono-directional filament tape with high viscosity and long-term holding power. Suitable for heavy objects trapping; pipe strapping; pallets fixing; reinforced marine carton packaging.

### PERFORMANCE FEATURES :

JLT-6614A is a transparent and high strength filament tape. Chemical fiber contributes higher tensile strength and improved acrylic pressure-sensitive adhesive delivers stronger adhesion; high resistance to abrasion; impact resistance and high holding power.

### STORAGE CONDITION :

It's recommended to store in clean and dry place. Damaged packaging shall be prevented. Not stored with volatile solvent. The temperature of storage shall be 4°C to 26°C and the humidity shall be between 40% and 50%. Rotate inventory recommended.

The above properties and results obtained refer to the average values of laboratory testing carried out on the samples of Kingnode product. Kingnode does not guarantee testing accuracy and makes no guarantee of product performance, safety, or suitability, either expressed or implied, when used alone or in combination with other products. Kingnode strongly urges users to undertake independent testing in order to verify the suitability of the product for whatever intended use. Kingnode assumes no responsibility for any damage or injury sustained as a result of the use of its products.

### Kingnode America Inc.

3005 Breckinridge Blvd suite 200, Duluth, GA 30096. United States  
 Tel:+1 888-998-6866  
 info@kingnodetech.com  
 https://kingnodetech.com

