



JLT-698

Mono-Directional Clean Removal Filament Tape

Physical Properties	Standard	Metric	Test Method	
Reinforcement	Fiberglass			
Adhesive	Synthetic Rubber			
Backing	PET			
Color	Clear			
Total Thickness	7.1 mils	0.18 mm	ASTM D-3652	GB/T7125
Peel Adhesion 90°	79 oz/in	22 N/25mm	ASTM D-3330	GB/T2792
Holding Power	≥48h	≥48h	ASTM D-3654	GB/T4851
Tensile strength	236 lbs/in	1050 N/25mm	ASTM D-3759	GB/T7753
Elongation at Break	5-7%	5-7%	ASTM D-3759	GB/T7753
Service Tem.--Mini	14°F	-10°C	BC/BD-220SE	BC/BD-220SE
Service Tem.--Max	176°F	80°C	DHG-9055A	DHG-9055A

Description:

JLT-698 Backed with PET film and reinforced with glass fiber. It's high strength mono-directional filament tape with good resistance to abrasion; special adhesive left no residue after peeled off; suitable for bundling of wire rope of bridge; fixing household electrical appliances; furniture; steel rolling industry.

Performance Features:

JLT-698 is a transparent and high strength filament tape. Glass fiber contributes higher tensile strength and improved pressure-sensitive adhesive delivers stronger adhesion; good adhesion to the surface slightly stained by oil and without residue left; high resistance to abrasion; impact resistance and high holding power.

Storage Condition:

It's recommended to store in clean and dry place. Damaged packaging shall be prevented. Not stored with volatile solvent. The temperature of storage shall be 4°C to 26°C and the humidity shall be between 40% and 50%. Rotate inventory recommended.

Shelf Life:

1 years from the date of shipment

The above properties and results obtained refer to the average values of laboratory testing carried out on the samples of Kingnode product. Kingnode does not guarantee testing accuracy and makes no guarantee of product performance, safety, or suitability, either expressed or implied, when used alone or in combination with other products. Kingnode strongly urges users to undertake independent testing in order to verify the suitability of the product for whatever intended use. Kingnode assumes no responsibility for any damage or injury sustained as a result of the use of its products.

Kingnode America Inc.

3005 Breckinridge Blvd suite 200, Duluth, GA 30096. United States

Tel: +1 888-998-6866

info@kingnodetech.com

https://kingnodetech.com

