

ALLWOOD WHOLESALE PTY LTD

TEST REPORT

SCOPE OF WORK WPC Co-extrusion Modern decking


REPORT NUMBER 210723004SHF-001

TEST DATE(S) 2021-07-23 - 2021-08-02

ISSUE DATE 2021-08-02

PAGES 5

DOCUMENT CONTROL NUMBER LFT-APAC-SHF-OP-10k(May 1, 2021) © 2021 INTERTEK



Intertek Testing Services Shenzhen Ltd. Shanghai Fengxian Branch





Intertek Testing Services Shenzhen Ltd. Shanghai Fengxian Branch Plant 5, No. 6958 Daye Road, Fengxian District, Shanghai, China Tel: 021-61136116 Fax: 021-61189921 Website: www.intertek.com

Test Report

Statement

1. This report is invalid without company's special seal for testing on assigned page.

2. This report is invalid without authorized person's signature.

3. This report is invalid where any unauthorized modification indicated.

4.Don't copy this report in partial (except full copy) without any official approval in written by our company. This report is invalid without re-stamping the special seal for testing in copying report.

5.Any holder of this document is advised that this report is for the exclusive use of Intertek's Customer and is provided pursuant to the agreement between Intertek and its Customer. Intertek's responsibility and liability are limited to the terms and conditions of the agreement. This report was made with due care within the limitation of a defined scope of work and on the basis of information, materials and instructions received from the Customer or its nominated third parties. Intertek is under no obligation to refer to or report upon any facts or circumstances which are outside the specific instructions received and accepts no responsibility to any parties whatsoever, following the issue of the report, for any matters arising outside the agreed scope of the works. The tests results are not intended to be a recommendation for any particular course of action. Customer is responsible for acting as it sees fit on the basis of such results.

6.Intertek's written consent is required to use Intertek's name or logo on the object, product or service being tested. The observations and test results in this report relate only to the sample under test. This report alone does not indicate that the item, product or service has passed any Intertek certification program.

7. The report was digital signed by Shang Hai, Intertek Group plc, please using Adobe Acrobat Reader to verify the authenticity.



Intertek Testing Services Shenzhen Ltd. Shanghai Fengxian Branch Plant 5, No. 6958 Daye Road, Fengxian District, Shanghai, China Tel: 021-61136116 Fax: 021-61189921 Website: www.intertek.com

Test Report

Issue Date:	2021-08-02	Intertek Report No.	210723004SHF-001	
Applicant:	ALLWOOD WHOLESALE PTY LTD			
Address:	211/1 CENTENNIAL DRIVE CAMPBELLTOWN	NSW 2560		
Attn:	Lifeng Zhang			
Test Type:	Performance test, samples provided by the	applicant.		

Product Information

Product Name	WPC Co-extrusion Modern decking		Brand	/	
Sample	Good Condition		Sample Amount	3 pcs	
Description			Received Date	2021-07-21	
Sample ID		Model		Specification	
S210723004SHF.001		/		140x22mm	

Test Methods And Standards

Test Standard	AS 4586-2013 Appendix A
Specification Standard	/
Test Conclusion	The samples were tested according to the above standards, and the results are shown in the following page.

Note:

1. This report relates specifically to the sample(s) that were drawn and provided by the applicant or their nominated third party. The reported result(s) provide no warranty or verification on the sample(s) representing any specific goods and/or shipment and only relate to the sample(s) as received and tested.



gers Wang

Name: Eggers Wang Title: Project Engineer



Test Report

Issue Date:	2021-08-02	Intertek Report No.	210723004SHF-001
Test Items, Method ar	nd Results:		

Test Item:	Wet Pendulum Test
Test Method:	AS 4586-2013 Appendix A
Conditioning:	Condition the test specimens at $(23 \pm 2)^{\circ}$ C and $(50 \pm 5)^{\circ}$ relative humidity for 48 hours
Test Temperature:	23 °C
Slider:	Slider 55
Test Surface:	Wet condition
Test direction:	0°= parallel to length direction
	45°= angle of 45° with length direction or width direction
	90°= parallel to width direction

Test Item	Test Method	Test Re	sult	Class
Wet pendulum test AS 4586-2013 App		Direcition	Pednulum SRV	P4
	AS JERG 2012 Appondix A	0°	41	
	AS 4560-2015 Appendix A	45°	45	
		90°	44	

Note:

1. Class based on the lowest result of three directions.

2. Test surface and directions were included in Appendix A.

AS 4586 Wet Pendulum Test Classification of Pedestrian Surface Materials

Class	Pednulum SRV		
Class	Slider 96	Slider 55	
P5	>54	>44	
P4	45-54	40-44	
Р3	35-44	35-39	
P2	25-34	20-34	
P1	12-24	<20	
РО	<12	/	




Test Report

Issue Date: 2021-08-02

Intertek Report No. 210723004SHF-001

Appendix A: Sample Received Photo



Front/ Back View(Test Face)

Side View



Revision:

NO.	Date	Changes
210723004SHF-001	2021-08-02	First issue