

# IDEALSEAL NEUTRAL LM SILICONE (WHITE) TECHNICAL DATA SHEET

# **Idealseal Neutral LM Silicone (White)**

Premium all in one low modulus neutral silicone sealant for sanitary, building, glazing & façade joints



# **Description**

Idealseal Neutral LM Silicone combines premium MEKO-free low modulus neutral curing technology free of solvents and mineral oils with sanitary grade anti-fungal compounds to provide a watertight, low odour, non-shrinking, flexible, UV and weather resistant seal which resists mould and bacterial growth. The sealant has excellent primer-free adhesion to both porous and non-porous surfaces accommodating joint movement of + or - 25%. It is temperature resistant between - 50°C to +120°C and will not crack, harden or dry out.

### Uses

Idealseal Neutral LM Silicone was specifically developed for durable elastic sealing of connection and expansion joints both internally and externally. It is commonly used for sealing glazing systems including the bedding of double glazed units and perimeter pointing around window and door frames, sealing panels within cold stores, sealing sanitary joints in kitchens,

bathrooms and showers, sealing of curtain wall constructions and cladding. It is also compatible with most common building materials such as plastics, glass, glazed surfaces, cap beading, treated wood, metal profiles, concrete and brickwork.

### **Technical Detail**

	Base		2-Pentanone Oxime
	100% Modulus	DIN 53504 S2	0.35 N/mm <sup>2</sup>
	Application	@ Ø3mm/6.3	130g/min
	rate	bar	
	Application		+ 5°C to
	temperature	,	+40°C
	Curing time	@ +23°C/50% RH	2-3mm/24 hours
	Density	ISO 1183-1	1.22g/ml
	Elongation at break	DIN 53504 S2	550%
	Frost resistance		Up to -15°C
	during transportation		ορ to -13 C
	Joint movement		25%
	Shorea hardness	DIN 53505	19
	Skin formation	DBTM 10	8 minutes @ +23°C/50%RH
	Temperature		- 50°C to
	resistance		+120°C
	Tensile strength	DIN 53504 S2	1.30 N/mm <sup>2</sup>

# Colour

White

## **Packaging**

310ml x 12

# **Application**

Surfaces must be dry and dust free. Cut the cartridge seal and screw on nozzle which should be cut to required size. Gun the sealant firmly into joint ensuring no air is trapped behind. If required place masking tape along joint edges, removing within 5 minutes of application.



# IDEALSEAL NEUTRAL LM SILICONE (WHITE) TECHNICAL DATA SHEET

### Limitations

Not recommended for use on PE, PP, PMMA and PTFE.

### **Paintability**

Idealseal Neutral LM Silicone is not paintable. It is recommended to cover the edges of the joint you plan to paint with masking tape to prevent surface contamination by the silicone.

#### **Shelf Life**

In unopened original packaging between + 5°C and +25°C, shelf life up to 24 months from production date stated on the tube, store in a dry place

### Certifications



## **Health and Safety**

Safety data sheet (MSDS) must be read and understood before use of the product this is available on request and via www.idealsealants.com.

## Liability

The information given is the result of our tests and experience and is believed to be accurate and reliable. However as Ideal Sealants Limited cannot know all the uses its products may be put to, and as application methods are out of our control it is the user's responsibility to determine suitability of use.

### Disclaimer

All information in this document and in all our other publications (including electronic ones) is based on our current knowledge and experience and is the exclusive (intellectual) property of Ideal Sealants Ltd. No part of this document may be copied, shown to third parties, reproduced, communicated to the public or used in any other way without Ideal Sealants Ltd written consent. The technical information in this document serves as an indication and is non-exhaustive. Ideal Sealants Ltd is not liable for any damage, either directly or indirectly, due to (editorial) errors, incompleteness and/or incorrectness of this document. This includes, but is not limited to, incompleteness and/or incorrectness due to technological changes or any research conducted between the date of publication of this document and the date on which the product is acquired. Ideal Sealants Ltd cannot be held liable for any damage, either directly or indirectly, due to the use of the product(s) depicted in this document. The user must read and understand the information in this document and other documents relating to the products prior to the use of the product. The user is responsible for performing all the requisite tests to make sure that the product is suitable for its intended use. We have no influence in what way the product is applied and/or any circumstances relating to events occurring during storage or transport and therefore we do not accept any liability for damage whatsoever.