Cemfloor Complete Technical Data Sheet



Cemfloor Complete is a specially formulated ready to use self levelling cementitious floor screed and can be applied to a wide range of floors. Cemfloor Complete is a mixture of Cemfloor binder, cement, water and a kiln dried sand. Cemfloor Complete is a high performance screed which complies with EN 13813:2002 and is available in 25kg and 1000kg bags.

Key Features & Benefits

- > Thinner sections compared to traditional screeds.
- Minimal Drying Shrinkage (<0.5%)</p>
- ▶ Larger floor area without joints (up to 150m2 for unheated floors and 100m2 for heated floors.)
- > Foot Traffic after 24-48 hours.
- > Exceptional Thermal Conductivity
- > Can be applied in wet areas
- > Reduced Drying Times (Depending on drying conditions)
- > Self Compacting no voids around underfloor heating pipes
- ▶ No risk of contamination at concrete mixing plants
- > No surface laitance (Dust) after curing
- > Easy Installation (Reducing time & costs)

Substrate

Cemfloor Complete is designed for use as a bonded thick levelling screed on concrete, as a floating screed over thermal or acoustic insulation with a minimum compressive strength of 100kPa, or as an unbonded screed on top of a plastic membrane.

Mixing

A 25kg bag of Cemfloor Complete requires 3.4 – 3.8 litres of water. Add the pre-measured water to a clean bucket and slowly add the powder whilst mixing with an electric paddle. Mix until a smooth and lump free consistency is obtained. Do not add further water once mixed. Exceeding 3.8 litres of water per 25kg will result in water bleed, extended drying times, a weakened mix and poor surface finish.

N.B: Once mixed, Cemfloor Complete has a pot life of approximately 30 minutes at 23°C

Application

Cemfloor screeds should be used in accordance with BS 8204-7:2003 'Code of Practice for Pumpable Self-Smoothing Screeds'. To ensure a high quality screed it is recommended that application is carried out by a specialist screeding contractor who has been approved to place Cemfloor. The freshly poured screed will need to be levelled using a dappling bar, ensuring to dapple the surface in two passes at 90 degrees.

When Cemfloor screed is installed as per installation guidelines in a sealed/weather tight area; it will not require any curing agent sprayed onto its surface.

If the screed will be exposed to any wind/drafts or excessive sunlight then a suitable evaporation control spray (e.g. Cemfloor EC) may need to be sprayed onto the screed surface. Please contact our Technical Team for any further information.

Curing



After placing the floor should not be subjected to severe draughts, direct sunlight or heating for the first 24-48 hours. The room in which the screed has been placed should therefore be sealed during this time. The room should be ventilated after 24-48 hours by opening windows and doors during the day to aid the drying process.

Floor Coverings

Cemfloor Therm screed is compatible with all floor coverings, and all cementitious adhesives including fast track systems. The screeds moisture content should be measured before placing floor coverings to ensure that it is adequately dried. Cemfloor screed will not require any sanding to remove laitance. As part of the floor finish installation, it is recommended that the surface of the screed be lightly prepared to clean and remove any building residue/contamination to ensure that there is a good key to receive subsequent floor coverings.

Technical Information

Cemfloor Complete is produced in an ISO 9001 quality-controlled environment. Cemfloor Complete meet the requirements of EN 13813:2002 'Screed Material for Floor Screeds'.

| Screed Specification | EN 13813:2002 |
|----------------------------|---|
| Compressive Strength | C25 |
| Flexural Strength | F5 |
| Minimum Thickness | Bonded: 20mm Unbonded: 30mm Floating: Domestic: 35mm Commercial: 40mm Over underfloor heating pipes: 25mm above pipes |
| Shrinkage (28 Days) | <0.5% |
| Flow Rate | 230-260mm |
| Fresh Density | 2100-2200kg / m3 |
| Surface Flatness | Min SR2 |
| ISCR Test | Category A |
| Open to Light Foot Traffic | 24-48 Hours |
| Maximum Bay Sizes | Non-Heated Floors =150m2 Heated Floors =100m2 |