

Test Report

No. SH9135012/CHEM

Date: Jul. 15, 2009

Page 1 of 3

NEOFLAM INC.

5TH FLOOR, #880-10, HWAGOK-DONG, GANGSEO-GU, SEOUL, KOREA

The following sample(s) was/were submitted and identified by/on behalf of the client as:

Sample Name

: NEOFLAM COOKWARE WITH ECOLON COATING (CERAMIC COATING)

SGS Ref No.

: SHD002917780

Sample Receiving Date: Jul.10, 2009 **Testing Period**

: Jul.10-15, 2009

Test Requested

: With reference to French Décret 92-631 and French recommendation DGCCRF

2004-64.

For material: Ceramic-Extractable Lead and Cadmium content.

Test Method

: As specified by client, with reference to EEC Directive 84/500/EEC.

Analysis was performed by Atomic Absorption Spectrometer.

Test Results

: Please refer to next page.

Signed for and on behalf of SGS-CSTC Chemical Laboratory

> Sandy Hao Lab Manager

This document is issued by the Company under its General Conditions of Service printed overleaf or available on request and accessible at http://www.sgs.com/terms_and_conditions. htm. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Centago in findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document experience of the context of th

es Co., Ltd. 3rd Building, No. 889, Yishan Road, Shanghai, China nemical Laboratory. 中国・上海・宜山路889号3号楼

200233 邮编: 200233 tE&E:(86-21) 61402553 fE&E:(86-21) 64953679



Test Report

No. SH9135012/CHEM

Date: Jul. 15, 2009

Page 2 of 3

Test Results

Metal cookware with black ceramic

| | | | | | Category 3 Limit |
|------------------------------------|--------|--------|--------|--------|------------------|
| Released Lead (mg/l) | < 0.1 | < 0.1 | < 0.1 | < 0.1 | 1.5 |
| Released Cadmium (mg/l) | < 0.01 | < 0.01 | < 0.01 | < 0.01 | 0.1 |
| Volume of 4% Acetic acid used (ml) | 5102 | 5102 | 5102 | 5102 | |
| Depth (mm) | 91 | 91 | 91 | 91 | |
| Diameter (mm) | 307 | 307 | 307 | 307 | |

Remark:

Definition For ceramic wares according to French recommendation DGCCRF 2004-64:

Articles that cannot be filled and articles that can be filled, the internal depth of which does

not exceed 25 mm.

Category 2

Articles, not in categories 1 or 3, which can be filled

Cooking ware; packaging and storage vessels having a capacity of more than three liters

Lip and rim area for drinking utensils: With coating or colour within 20 mm along the lip and Rim area which is different from the colour of the interior cavity.

Note:

- 1. mg/l=milligram per litre
- 2. mg/article = milligram per article
- 3. <= less than

This document is issued by the Company under its General Conditions of Service printed overleaf or available on request and accessible at http://www.sgs.com/terms_and_conditions.htm. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Centago findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document of sections of the content of the content of the content of the content of the law.

Unless otherwise stated the results shown in this test report refer only to the sample(s) tested. This document cannot be reproduced except in full, without prior approval of the Company.

ces Co., Ltd. 3rd Building, No. 889, Yishan Road, Shanghai, China nemical Laboratory. 中国・上海・宜山路889号3号楼

200233 邮编: 200233 tE&E:(86-21) 61402553 fE&E:(86-21) 64953679



Test Report

No. SH9135012/CHEM

Date: Jul. 15, 2009

Page 3 of 3

Sample Photo:



SGS authenticate the photo on original report only

*** End of Report ***

This document is issued by the Company under its General Conditions of Service printed overleaf or available on request and accessible at http://www.sgs.com/terms_and_conditions.htm. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Cermany indicates t

es Co., Ltd. 3rd Building, No. 889, Yishan Road, Shanghai, China hemical Laboratory. 中国・上海・宜山路889号3号楼

200233 邮编: 200233 tE&E:(86-21) 61402553 fE&E:(86-21) 64953679