



DURA+™
Interior CABINET, DOOR & TRIM
ULTRA PREMIUM PRIMER
DADR00-0-WH-1



≤ 50 g/L VOC**

DESCRIPTION: Dunn-Edwards DURA+ Interior Wood Primer is designed for use on wood, hardboard and wallboard, making it ideal for use on new wood cabinets, doors, and trim. It can also be applied over previously painted wood surfaces. This water-based ultra-premium primer is ultra-low VOC and fast drying. It sands easily, resists household stains, and provides excellent hide and sealing qualities.

PRODUCT INFORMATION

SOLVENT TYPE: Waterborne | **RESIN TYPE:** 100% acrylic

FINISH (ASTM D 523): 5–10% on a 60° meter

COLORS: White

VISCOSITY@77°F/25°C (ASTM D 562): 98–106 KU

MAXIMUM VOC CONTENT | **MAXIMUM RAVOC** (Reactivity-Adjusted VOC)
 50 g/L (as supplied) | 15 g/L

SOLIDS BY VOLUME (ASTM D 2697) | **SOLIDS BY WEIGHT**
 37.9% ± 2% | 52.5% ± 2%

WEIGHT PER GALLON (ASTM D 1475): 10.88 lbs.

COMPOSITION BY WEIGHT

Pigment—30.5% | **Vehicle—69.5%**
 Prime pigments* 15.6 | Resin Solids..... 20.3
 Reinforcing pigments..... 14.9 | Water & additives 49.2

*Prime pigments include all pigments directly adding to the hiding power of this paint.

RECOMMENDED FILM THICKNESS PER COAT

Wet: 4 mils | Dry: 1.5 mils

PRACTICAL COVERAGE PER COAT AT RECOMMENDED DRY FILM THICKNESS

Approximately 350–400 sq. ft. per gallon, depending on surface conditions and application techniques.

THINNING RECOMMENDATION: This coating is intended to be applied without thinning or diluting under normal environmental and application conditions. If necessary to maintain good workability, add up to 1/4 pint (4 fl. oz.) of clean water per gallon of coating.

AVERAGE DRY TIME@77°F/25°C (ASTM D 1640)

To touch: 30-60 minutes | Recoat: 1–2 hours
 Dry times and recoat times are temperature, humidity and film thickness dependent.

APPLICATION EQUIPMENT: Airless spray, brush, roller,

AIRLESS SPRAY	BRUSH	ROLLER
PRESSURE: 1800-2500psi	Nylon/Polyester	1/4"-3/8" nap
TIP: Wood .013"-.015" Drywall .015"-.019"		

PACKAGING: One-gallon, five-gallon containers

STORAGE: Store in a dry area. Protect from freezing. Protect from temperatures above 110°F for extended periods of time. Extreme temperatures may cause paint to become unusable. See *Paint Storage Best Practices* Technical Bulletin at dunnedwards.com for more information.

CLEANUP: Warm, soapy water

DISPOSAL: For information on local options to dispose of unwanted leftover paint, call Dunn-Edwards Customer Service at 1-888-DEPAINT or visit www.dunnedwards.com. **Do not mix with other products.**

CONFORMS TO: ARB 2007 SCM & CALGreen 2019; CDPH Standard Method v1.2; LEED 2009 IEQ Credit 4.2; MPI Approved Product #39; CRGI Green Wise Certified; FDA Guidelines for Coatings.

SAFETY DATA SHEET: Available at www.dunnedwardsdura.com

SURFACE PREPARATION: All surfaces must be cured, clean, dry, and free from dirt, dust, rust, stains, grease, oil, mildew, wax, efflorescence, bond-breakers, and other contaminants. Remove all loose, peeling, or chalky paint by sanding, scraping, or other appropriate methods. Repair all cracks, holes, and other surface imperfections with a suitable patching material. Repaired surfaces should then be sanded smooth and dusted clean. Glossy surfaces should be dulled to provide a roughened surface for good adhesion.

SPECIAL INSTRUCTIONS

- **CAUTION!** Scraping or sanding surfaces of older buildings (especially pre-1978) may release dust containing lead or asbestos. EXPOSURE TO LEAD OR ASBESTOS CAN BE VERY HAZARDOUS TO YOUR HEALTH. Wear a NIOSH-approved N95 particulate filter mask to avoid breathing dust. Use a HEPA vacuum for cleanup, and finish by water-washing all surfaces. For more information, see Dunn-Edwards brochure on "Surface Preparation Safety" or call U.S. EPA's lead hotline at 1-800-424-LEAD, or visit www.epa.gov/lead or / asbestos, or contact your state or local Health Agency.
- This product can neither cause nor prevent or cure the growth of mold, mildew, or other forms of fungus. Excessive moisture and inadequate ventilation are the main conditions that promote their growth. Correct any such conditions before painting.
- Allow all skim coats to cure for 3 days before sealing.
- Do not apply when the air or surface temperature is below 50°F.

HEALTH & SAFETY: CAUTIONS! INHALATION OF SPRAY MIST OR SANDING DUST MAY BE HARMFUL. Use only with adequate ventilation. Avoid breathing vapors, spray mist and sanding dust. Wear NIOSH-approved N95 particulate filter mask when spraying or sanding. Avoid contact with skin and eyes. Do not ingest. Close container after each use. **FIRST AID:** If swallowed, immediately give 1 or 2 glasses of water to drink – for emergency information, call 1-800-222-1222. If having difficulty breathing, move to fresh air. For eye contact, immediately flush with water for 15 minutes. For skin contact, wash thoroughly with soap and water.

• **KEEP OUT OF REACH OF CHILDREN** •

Ingredient (CAS #): Water (7732-18-5); Copolymer Resin (Proprietary); Titanium Dioxide (13463-67-7); Nepheline Syenite (37244-96-5); Talc, Non-Asbestos (14807-96-6).

⚠ **WARNING:** Cancer and Reproductive Harm – www.P65Warnings.ca.gov