

Epifanes Clear Varnish

One-comp. classic high gloss yacht varnish + extra UV filter



PRODUCT DESCRIPTION

Extreme high gloss, unique flow characteristics and high build capacity. The UV filter protects the wood for discoloration. Its flexibility prevents cracking on working wood. This varnish is famous for its high gloss retention, long lasting properties, even in tropical climates.

Field of use: New work on bare solid wood (mahogany, meranti, Oregon pine) and plywood both for inside and outside above the waterline. Maintenance of intact existing (one- and two-component) varnishes regardless of brand. Not suited for direct use on epoxy resin unless the amine blush from the epoxy has been removed first.

PRODUCT INFORMATION

Type	Oxidative drying
Base	Phenolic resin / Alkyd resin / Tung Oil
Gloss	High gloss
Colour	Transparent amber
Density at 68°F.	0,9138 g/cm ³
Viscosity	50 seconds ISO-cup 4 mm
Solids Contents	52 ± 2 vol. %
VOC-level	370 g/l
Packing	250ml. - 500ml. - 1000ml. - 5000ml.
Shelf life	3 years in closed original container if stored in a location with temperatures between 41-86°F
Rec. filmthickness	2 - 2.5 mil wet = 1 –1.5 mil dry
Thinner brush	Epifanes Brushthinner for Paint & Varnish or 100% mineral spirits (NOT low VOC).
Thinner spray	Epifanes Spraythinner for Paint & Varnish or denatured alcohol
Thinning in general	Thinning ratio depends on product temperature and working area. Avoid overthinning. For thinning ratios, refer to the Epifanes varnish systems.

Drying times	50°F.	59°F	68°F	77°F
Dust dry	5 hours	4 hours	3 hours	2 hours
Sandable	40 hours	30 hours	24 hours	20 hours
Recoatable	40 hours	30 hours	24 hours	20 hours

The above mentioned drying times are indicative at 65% RAH and 1 mil dry film thickness. Drying also depends on ventilation and applied wet film thickness. A higher wet film thickness and/or poor ventilation results in longer drying times. Especially horizontal parts may take longer to dry due to high wet film thickness. Allow each varnish coat sufficient time to dry. Do not apply wet-on-wet!

Substrate
 Bare wood : degreased and sanded 180G.
 For maximal impregnation into the wood grain, thin first coat 40-50% .

 Maintenance of varnish: degreased and sanded 220-320G.
 For a good grip, thin first coat 10% .



Epifanes Clear Varnish

One-component classic high gloss yacht varnish + extra UV filter

APPLICATION

Conditions during application **Temperature** minimal 47°F. - maximal 86°F.
Relative air humidity minimal 50% - maximal 85%

Best results are achieved by longhaired soft brush or by air spray. Because of the required wet film thickness application by roller is not advised. Evenly distribute the varnish over the surface and tip off along the wood grain. Avoid retipping. Do not apply wet-on-wet. Do not apply excessive wet film thickness to avoid the formation of curtains and drying problems. Avoid varnishing in direct sunlight or too much wind. A rapid loss of solvents will occur under these conditions and decrease the flowing ability. Avoid large difference in temperature of the product, surface to be varnished and working area. In case the product "pulls" and is difficult to apply, 10% Epifanes Brushthinner may be added. To retrieve the original colour of the wood, Epifanes Mahogany Stain or Epifanes Teak Stain may be added to the varnish up to 10%. After drying, lightly sand the surface with 320G or Scotch Brite. Always sand by hand along the wood grain.

Guidelines for spray application:

Thinning volume	Nozzle	Pressure	Visco DIN-cup 4 mm
15-20%	1.2 mm - 1.5 mm	30-45 psi	20-24 sec.

SYSTEM BUILD UP - BRUSHING

	Step 1	Step 2	Step 3	Step 4
Product	EPIFANES Clear Varnish	EPIFANES Clear Varnish	EPIFANES Clear Varnish	EPIFANES Clear Varnish
Numb. of coats	1	1	1	4 of more
Thinner	EPIFANES Brushthinner PV	EPIFANES Brushthinner PV	EPIFANES Brushthinner PV	EPIFANES Brushthinner PV
Thinning ratio	50%	25%	15%	0-5%
Drying time 68°F.	24 hours	24 hours	24 hours	24 hours
Sanding grit	Dry 220G - sand by hand	Dry 220G - sand by hand	Dry 220G - sand by hand	Wet or Dry 320G / Scotch Brite
Remarks	First penetrating varnish coat. For full varnish penetration inside the wood fibres, apply this first coat heavily thinned.	Second penetration varnish coat. Apply this second coat approx. 25% thinned Sand by hand along the wood grain.	Third penetration varnish coat. Apply this second coat approx. 15% thinned Sand by hand along the wood grain.	At least 4 finishing coats are required. In warmer climates with high UV-levels, at least 6 or more full bodied finishing coats are required for sufficient protection.

Theoretical coverage 150ft² per liter @ 1 mil dry filmthickness
Practicle coverage Dependent on condition of substrate, loss of material due to factors such as application technique, shape of object, circumstances during application.

Recoatibility with other Epifanes varnishes

Epifanes Woodfinish Gloss	High gloss alternative
Epifanes Woodfinish Matte	Matt finish for interior / exterior use
Epifanes Rubbed Effect Varnish	Satin finish for interior use
Epifanes Aqua Marine Interior Varnish	Water based satin finish for interior use
Epifanes Rapidcoat / Rapidclear	Semi gloss alternative

Safety The user of this product should obey all national laws and legislation concerning health, safety and environmental hazard. For more information on health and safety, refer to the Material Safety Data Sheet of this product.

Although the facts and suggestions in this product information sheet are based on our own research and field experiences and are believed reliable, we cannot simply be held responsible for performance or results obtained through the use of this product. Ineffectiveness or other unintended consequences may result, because of such factors as weather, conditions, presence or other materials or the manner of preparation, use or application all of which are beyond W. Heeren & Zoon's control. All such risks are assumed by user.

DISCLAIMER OF WARRANTIES. Seller makes no express warranties. THE IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE ARE EXCLUDED. In the event a warranty is created by law, buyer's EXCLUSIVE REMEDY shall be the replacement of any defective product. No other remedy (including, but not limited to, incidental or consequential damages for lost profits, lost sales, injury to person or property, or any other incidental or consequential loss) shall be available to buyer.

W. Heeren & Zoon BV
 PO box 166
 1430 AD Aalsmeer
 Netherlands
 Phone +31 297 – 360366
 info@epifanes.nl
 www.epifanes.nl

