

Epifanes Nautiforte Yacht Paint

Non yellowing yacht coating



PRODUCT DESCRIPTION

High gloss non-yellowing yacht coating. The siliconized resin prevents yellowing in the long run and creates a long lasting gloss retention and minimal dirt fixation. This paint is very easy to apply at all temperatures. Due to the blend of high quality pigments, it gives a high covering power.

Field of use: In a new system for wood, steel and aluminium. FRP in combination with the appropriate primer. Also suited for maintenance of existing intact one-and two-component paint systems above the waterline regardless of brand.

PRODUCT INFORMATION

Type	Oxidative drying
Base	Siliconized alkyd resin
Gloss	High gloss
Colour	White - Cream #24
Density at 68°F.	1,20 g/cm ³ depending on colour
Viscosity	35 seconds ISO-cup 6 mm
Solids Contents	55 ± 2 vol. %
VOC-level	307 g/l
Packing	750ml. - and white also in 2000 ml
Shelf life	In closed unopened container stored in a dry room at temperatures between 41 - 86°F approx. 3 years.
Rec. film thickness	2.5-3 wet = 1.5 mil dry
Thinner brush	Epifanes Brushthinner for Paint & Varnish or 100% Mineral Spirits (NOT low VOC.)
Thinner spray	Epifanes Spraythinner for Paint & Varnish or denatured alcohol
Thinning in general	Thinning ratio depends on product temperature and working area. Avoid overthinning. For thinning ratios, refer to the Epifanes paint systems.

Drying times	50°F.	59°F.	68°F.	77°F.
Dust dry	3 hours	2 hours	1 hour	45 minutes
Sandable/Recoatable	36 hours	24 hours	18 hours	12 hours

The above mentioned drying times are indicative at 65% RAH and 1.5 mil dry film thickness. Drying also depends on the amount of ventilation and applied wet film thickness. Higher wet film thickness and/or poor ventilation results in longer drying times. Especially horizontal parts may take longer to dry due to high wet film thickness. Allow each paint coat sufficient time to dry. Do not apply wet-on-wet!

Theoretical coverage 150ft² per liter @ 1.5 mil dry film thickness

Practicle coverage Dependent on condition of substrate, loss of material due to factors such as application technique, shape of object, circumstances during application.



Epifanes Nautiforte Yacht Paint

Non yellowing yacht coating

APPLICATION

Conditions during application **Temperature** minimal 47°F. - maximal 86°F.
Relative air humidity minimal 50% - maximal 85%

Best results are achieved by roller, longhaired soft brush or by spray. Evenly distribute the paint over the surface and do not retipp. Do not apply wet-on-wet. Do not apply excessive wet films to avoid the formation of curtains and drying problems. Avoid painting in direct sunlight or much wind. A rapid loss of solvents will occur under these conditions and will decrease the flowing ability. The maximum difference in temperature between the surface and the paint is 38°F. In case the product “pulls” and is difficult to apply, 10% Epifanes Brush thinner may be added. After drying, lightly sand the surface with 320G or Scotch Brite before applying the next coat. Always sand by hand.

Guidelines for spray application:

Thinning volume	Nozzle	Pressure	Visco DIN-cup 4 mm
5-15%	1.2 mm - 1.5 mm	30-37 psi	20-22 sec.

Substrates	Bare GRP	Clean and degreased with Epifanes Fibreglass Prep Cleaner Sanded with 220G
	Bare wood	Clean, dry and degrease with Epifanes Spraythinner for Paint & Varnish Sanded with 220G
	Bare Steel	Clean, dry, free of corrosion and degreased with Epifanes Cleaning Solution Sanded with 60G
	Existing paintwork	Well bonding, dry and degreased with Epifanes Spraythinner for Paint & Varnish Sanded with 220G
Appropriate primer	All substrates	: Epifanes Multi Marine Primer - Epifanes Undercoat
	Wood	: Epifanes Woodprimer.
	New aluminium	: Epifanes Washprimer AQ (do not sand)

GRP	Steel	Wood	Aluminium
1 - 2 primer coats	3 primer coats	1 - 2 primer coats	1 - 2 primer coats

After curing, sand each primer coat with 220G before applying finishing coats

System build up After priming, finish with 3 full bodied coats of Epifanes Nautiforte. Lightly sand between coats with 320G or Scotch Brite. For further information about the recommended Epifanes system build up visit our website and download the step-by-step system information.

Theoretical coverage 150ft² per liter @ 1.5 mil dry film thickness
Practicle coverage Dependent on condition of substrate, loss of material due to factors such as application technique, shape of object, circumstances during application.

Recoatibility with other Epifanes products

Epifanes Mono-urethane Yacht Paint	Epifanes Satin Finish
Epifanes Non-skid deck coating	Epifanes Flat Black
Epifanes Yacht Enamel	Epifanes Waterline Paint

Safety The user of this product should obey all national laws and legislation concerning health, safety and environmental hazard. For more information on health and safety, we refer to the Material Safety Data Sheet of this product.

Although the facts and suggestions in this product information sheet are based on our own research and field experiences and are believed reliable, we cannot simply be held responsible for performance or results obtained through the use of this product. Ineffectiveness or other unintended consequences may result, because of such factors as weather, conditions, presence or other materials or the manner of preparation, use or application all of which are beyond W. Heeren & Zoon's control. All such risks are assumed by user.

DISCLAIMER OF WARRANTIES. Seller makes no express warranties. THE IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE ARE EXCLUDED. In the event a warranty is created by law, buyer's EXCLUSIVE REMEDY shall be the replacement of any defective product. No other remedy (including, but not limited to, incidental or consequential damages for lost profits, lost sales, injury to person or property, or any other incidental or consequential loss) shall be available to buyer.