Technical datasheet EN-004

MARCH 2022

Epifanes Rubbed Effect Varnish

One component interior varnish with beautiful satin sheen













PRODUCT DESCRIPTION

Epifanes Rubbed Effect Varnish is quick drying, scratch resistant one component interior varnish based on urethane alkyd resins. This varnish gives a very pleasant warm satin look. It provides great protection against alcohol and household chemicals.

Field of use: As a satin final coat in a new system or as a maintenance satin varnish over an existing varnish system. Suited for application on virtually every varnish. On bare wood always start with several high gloss varnish build up coats. The high gloss varnish will fill the wood grain faster and the incorporated UV filter of the high gloss varnish will also protect the wood against discolorisation.

PRODUCT INFORMATION

Type Oxidative drying

Base Urethane/alkyd resin

Gloss Satin

Colour Transparent amber

Density at 68°F. 0,910 g/cm³

Viscosity 45 seconds IS0-cup 4 mm

Solids Contents 44 ± 2 vol. %

VOC-level 467 g/l

Packing 500ml. - 1000ml. - 5000ml.

Shelf life 3 years In closed unopened container stored in a dry location at temperatures between

41-86°F.

Rec. filmthickness 2.5 mil wet = 1 mil dry

Thinner brush Epifanes Brushthinner for Paint & Varnish or 100% mineral spirits (NOT low VOC).

Thinner spray Epifanes Spraythinner for Paint & Varnish or denatured alcohol

Thinning in general Thinning ratio depends on temperature of product and working area. Avoid overthinning. For

thinning ratios, see the Epifanes varnish system.

Drying times	50°F.	59°F.	68°F.	77°F.
Dust dry	3 hours	2 hours	1 hour	45 minutes
Sandable	24 hours	18 hours	12 hours	10 hours
Recoatable	24 hours	18 hours	12 hours	10 hours

The above mentioned drying times are indicative at 65% RAH and 1 mil dry film thickness. Drying also depends on ventilation and applied wet film thickness. Higher wet film thickness and/or poor ventilation results in longer drying times. Especially horizontal parts may take longer to dry due to high wet film thickness. Allow each varnish coat sufficient time to dry. Do not apply wet-on-wet.

Substrate New system: Clean the previously applied high gloss varnish and sand with 320G. Apply Epi-

fanes Rubbed Effect Varnish in 2 coats.

Existing system: Clean the varnish system and sand with 320G. Apply 2 coats of Rubbed Effect Varnish. Lightly thin the first coat to get a better bond with the varnish system in place.

W. Heeren & Zoon BV PO box 166 1430 AD Aalsmeer Netherlands Phone +31 297 – 360366 info@epifanes.nl www.epifanes.nl



1

Technical datasheet EN-004

MARCH 2022



One component interior varnish with beautiful satin sheen

Nozzle



Visco DIN-cup 4 mm

APPLICATION

Conditions during application Temperature Relative air humidity

Thinning volume

minimal 47°F. - maximal 86°F. minimal 50% - maximal 85%

Pressure

Best results are achieved by using a longhaired soft brush or by air spray. Because of the required wet film thickness application by roller is not advised. Evenly distribute the varnish over the surface and tip off along the wood grain. Avoid retipping. Do not apply wet-on-wet. Do not apply excessive wet film thickness to avoid the formation of curtains and drying problems. Avoid varnishing in direct sunlight or much wind. A rapid loss of solvents will occur under these conditions and this will decrease the flow. Avoid large difference in temperature of the product, surface to be varnish and working area. In case the product "pulls" and is difficult to apply, 10% thinner may be added. To retrieve the original colour of the wood, up to 10% Epifanes Mahogany Stain or Epifanes Teak Stain may be added to the varnish. After drying, lightly sand the surface with 320G or Scotch Brite. Always sand by hand along the wood grain.

Guidelines for spray application:

1:	5-20%	1.2 mm - 1.5 mm	30-45 psi	20-24 sec.		
SYSTEM BUILD UP						
	Step 1	Step 2	Step 3	Step 4		
Product	EPIFANES Clear Varnish	EPIFANES Clear Varnish	EPIFANES Clear Varnish	EPIFANES Rubbed Effect Varnish		
Numb. of coats	1		1 or more	1-2		
Thinner	EPIFANES Brushthinner PV	EPIFANES Brushthinner PV	EPIFANES Brushthinner PV	EPIFANES Brushthinner PV		
Thinning ratio	25-50%	10-25%	0-5%	0-5%		
Drying time 68°F.	24 hours	24 hours	24 hours	12 hours		
Sanding grit	Dry 220G - sand by hand	Dry 220G - sand by hand	Dry 320G by hand or Scotch Bright	Wet or dry 320G by hand or Scotch Bright.		
Remarks	First penetrating varnish coat. For full varnish penetration into the wood fibres apply this first coat heavily thinned.	Second penetrating varnish coat. Do not sand too heavy, but enough to create good grip for the next coat.	In case of openporic wood more gloss coats may be needed. Avoid heavy sand- ing, but sufficient enough to create good grip for the next coat of Epifanes Rubbed Effect Varnish.	Lightly sand between coats		

Theoretical coverage Practicle coverage

150ft² per liter @ 1 mil dry filmthickness

Epifanes Woodfinish Gloss

Dependent on condition of substrate, loss of material due to factors such as application technique, shape of object, circumstances during application.

Recoatbility with other Epifanes varnishes

Epifanes Clear Varnish High gloss finish

Epifanes Woodfinish Matte Matt finish for interior or exterior

Epifanes Aqua Marine Interior Varnish

Water based satin finish alternative for interior use

Epifanes Rapidcoat / Rapidclear Semi gloss finish

Safety

The user of this product should obey all national laws and legislation concerning health, safety and environmental hazard. For more information on health and safety, we refer to the Material Safety Data Sheet of this product.

High gloss finish

Allthough the facts and suggestions in this product information sheet are based on our own research and field experiences and are believed reliable, we cannot simply be held responsible for performance or results obtained through the use of this product. Ineffectiveness or other unintended consequences may result, because of such factors as weather, conditions, presence or other materials or the manner of preparation, use or application all of which are beyond W. Heeren & Zoon's control. All such risks are assumed by user.

DISCLAIMER OF WARRANTIES. Seller makes no express warranties.

THE IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE ARE EXCLUDED. In the event a warranty is created by law, buyer's EXCLUSIVE REMEDY shall be the replacement of any defective product. No other remedy (including, but not limited to, incidental or consequential loss) shall be available to buyer.

W. Heeren & Zoon BV PO box 166 1430 AD Aalsmeer Netherlands Phone +31 297 – 360366 info@epifanes.nl www.epifanes.nl

