



Marine Spar Varnish TDS

DESCRIPTION

System Three Marine Spar Varnish is designed to provide durable UV protection for demanding marine applications. It contains state of the art UV absorbers, which will keep wood looking beautiful even with constant exposure to strong sunlight. It's also resistant to scratching and marring, as well as many cleaners and solvents. Unlike most varnishes, System Three Marine Spar Varnish is formulated to dry over a wide variety of epoxy resin systems.

Physical Properties:	
Viscosity @ 77°F (25°C) CPS	Gloss – 150 Satin – 250
Density	7.6 lbs./gal.
Color	Amber
VOC Content	<450 grams/liter
Gloss Level @ 60°	Gloss – 90-95% Satin – 30-35%
Solids by Weight	50%

Other Information:	
Application Temperature Range	50°F-95°F (10°C-35°C)
Dry Time	4-6 hours
Recoat Time w/o Sanding	12-24 hours
Full Cure	14 days
Coverage Rate	400-450 ft ² /gal.

For health and safety information concerning this product, please refer to the SDS sheets for Marine Spar Varnish at systemthree.com.