Technical Data Sheet

RotFix Epoxy TDS

DESCRIPTION

S-1 Sealer is a marine two-part clear penetrating epoxy sealer. It's a superb waterproof sealer/primer for wood, metal, concrete, and reinforced polyester. An added plus is the easy 1:1 mix ratio and an extended 24-hour pot life. S-1 is ready to use with no thinning required. It displays excellent wetting properties on most surfaces. It can be applied with a brush, roller, or spray equipment. S-1 is completely waterproof and suitable for use above or below the waterline.

| Individual Component Properties: | | | | |
|----------------------------------|-----------|-----------------------------|-------|--|
| Resin Properties: | | Hardener Properties: | | |
| Viscosity @ 77°F (25°C) cps | 52 | Viscosity @ 77°F (25°C) cps | 25 | |
| Density | 8.07 | Density | 7.31 | |
| Color | Colorless | Color | Amber | |
| VOC Content | 525 | VOC Content | 553 | |

| Mixed System Properties: | | |
|---|-------------|--|
| Mixed Viscosity (at room temperature) cps | 42 | |
| Mix Ratio By Volume (Resin:Hardener) | 1:1 | |
| Mix Ratio By Weight (Resin:Hardener) | 100:94 | |
| Pot Life | 24 hours | |
| Minimum Application Temperature | 60°F(15°C) | |
| Maximum Working Temperature | 90°F (32°C) | |
| Recoat Time w/o Sanding @ 70°F (21°C) | 12-24 hours | |
| Time To Sand @ 70°F (21°C) | 24 hours | |

| Cured Properties: | |
|-------------------------|--------|
| Full Cure @ 70°F (21°C) | 3 Days |

For health and safety information concerning this product, please refer to the SDS sheets for S-1 at systemthree.com.