



NO2310T

Tri-Layer One Way Vision

Description:

Film: 120micron; black & white PVC film
Adhesive: Transparent adhesive
Liner: 75gsm perforated paper+70gsm PEK paper
Width: 0.98/1.06/1.27/1.37/1.52m

Features:

1. One side visual, sun-shade and privacy protection; Hole size 1.60mm, perforation 40%;
2. Stable ink absorption and excellent dimensional stability.

Applications:

1. Applicable to glass surface, also applicable to transparent acrylic, PVC, PET transparent panels;
2. This product is recommended to use UV printing; also suitable for various solvent ink and Eco-solvent ink.

Technical Data:

Testing condition: Indoor temperature $23\pm 2^{\circ}\text{C}$; Relative humidity $50\pm 5\%$; Use aluminum, glass, steel plate as the base material for testing.

Test Items	Units	Test method	Average value
Thickness PVC	Micron	GB/T6672-2001	120 ± 10
Weight-Liner	g/m^2	GB4669-1995	130 ± 10
Weight-finished product	g/m^2	GB4669-1995	245 ± 20
24h, 180°peel	N/25mm	FTM 1	≥ 4
Dimensional stability MD	mm	FTM 14	≤ 1.5
Dimensional stability CD	mm	FTM 14	≤ 1.0
Tensile strength MD	N/25 mm	GB/T1040.1-2006	≥ 25
Tensile strength CD	N/25 mm	GB/T1040.1-2006	≥ 20
Construction Temperature	$^{\circ}\text{C}$		$20\pm 10^{\circ}\text{C}$
Applicable Temperature	$^{\circ}\text{C}$		-20~ +70

- All technical data is subject to change without prior notice.

Storage Condition:

All NAR products always need to be stored in the original packing and with the original protection materials, preferably stored hermetically, no more than 6 layers if stored horizontally. Do not expose in direct sunlight or heat sources. Shelf life will be one year with temperature of $25\pm 10^{\circ}\text{C}$ and relative humidity of $50\pm 10\%$.

Production and Application Environment:

Production environment: temperature of $25\pm 5^{\circ}\text{C}$, relative humidity of $50\pm 10\%$, clean dust-free environment without suspended matter; Please move the materials to the printing environment 24 hours before printing. Test prior to use and remain enough edge margins when printing.

Application environment: temperature of $20\pm 10^{\circ}\text{C}$, relative humidity of $50\pm 10\%$; Pasting on flat, smooth and clean surface



Linea 146 S.A. de C.V. Castilla #54, Centro de Azcapotzalco, Azcapotzalco, C.P. 02000, CDMX
RFC: LCC190308QA4 Tel: (+5255) 1742 2166 ó 67 E-mail: ventas@faunadigital.com Website: www.linea146.com

without floating dust and shedding; It is necessary to take more than 2 hours for maintenance before laminating.

Warranty Condition:

1. One year shelf life: stored in suitable conditions, preferably use within 6 months;
2. One year prosecution period: from the product manufacture date, no-acceptance for overdue product.

Important Remark:

The information mentioned in this product data sheet is based upon test that were executed by NAR, and that we consider to be reliable. Environment humidity more than 70% in different district will decrease the printing result.

Product Application:

