



PROVAC

SALES

PHONE: 831-462-8900

FAX: 831-462-3536

WWW.PROVAC.COM

Krytox 1645, 16350

Technical Specifications

Other Krytox® Fluids for Vacuum Service*

Krytox®	Vapor Pressure, torr at 20°C (68°F) (Knudsen)	Kinematic Viscosity, mm ² /s (cSt at 20°C [68°F])	Pour Point, °C (°F)
16350	4×10^{-15}	3500	-5 (23)
1645	5×10^{-12}	450	-35 (-31)

