



## Dow Corning DC-976

### Technical Specifications

Typical Properties	DC-976
Color	light grey, translucent
Consistency - penetrometer, unworked (mm/10)	175 - 210
Bleed at 30 hours, 150°C (% max.)	3
Evaporation at 24 hours, 150°C (% max.)	1
Density at 25°C (g/ml)	1
Solidification Point (°C)	-40
Melting Point (°C)	None
Shelf Life (months)	60

## Features & Benefits

- silicone-based, odorless, translucent white-grey grease
- has good lubricating and sealing ability, as well as low volatility
- chemically resistant, and maintains its consistency over a wide temperature range
- insoluble in water, methanol, ethanol, acetone, glycol & glycerine

## Applications

- sealing & lubricating

