



PROVAC

SALES

PHONE: 831-462-8900

FAX: 831-462-3536

WWW.PROVAC.COM

Krytox FG 30, 32, 34, 36

Technical Specifications

Property	Krytox® FG 30	Krytox® FG 32	Krytox® FG 34	Krytox® FG 36
NLGI Grade	2	2	2	2
Thickener	PTFE	PTFE	PTFE	PTFE
Color	White, creamy consistency	White, creamy consistency	White, creamy consistency	White, creamy consistency
Base Oil Viscosity, cSt at 40°C (104°F)	30	160	240	738
Viscosity Index	121	125	134	158
Operating Range, °C (°F)	-60 to 154 (-76 to 310)	-36 to 204 (-33 to 400)	-30 to 260 (-22 to 500)	-10 to 300 (14 to 572)
Rust Prevention, ASTM D-1743	Pass	Pass	Pass	Pass
Four Ball EP Weld, ASTM D-2596, kg	Not tested	None	None	Not tested
Four Ball EP LWI, ASTM D-2596	Not tested	None	None	Not tested

Features & Benefits

- high temperature, extreme pressure, water-resistant greases
- provide stable performance in temperature extremes & are designed to reduce friction & wear while extending equipment life
- extremely resistant to water washout for bearings & other equipment
- can be used in both high & low temperature applications
- have superior extreme pressure properties & excellent adhesion

Applications

- food production, processing, handling, & packaging applications throughout the production line
- aerospace
- automotive
- industrial
- semiconductor