

**BANNER FLEX DE 13 ONZ (300 D X 500 D)**

ITEM	VALUE	UNIT	TEST METHOD
Fabric	(usual tenacity yarns) 100% PES(300d*500d)		DIN EN ISO2060
construction	18*12 Warp knitting 18*12	INCH	DIN60001
weight of fabric	57	gsm	DIN53352 BS3424method5B
weight of pvc coating	383	gsm	DIN53352 BS3424 method5B
breaking strength	warp: 635 weft: 451	N/5CM	DIN53354 BS3424method6A
tear strength	warp: 125 weft: 107	N	DIN53356 BS3424method7A
adhesion	50	N/5CM	DIN53357 BS3425 method9B
suitable temperature	-10 -----+70	°C	DIN53357 BS3425 method10
Lacquering	If the clients need Products can be reach:3555(Acrylic), 3483(Acrylic),7584(PVDF)		
Flammability	If the clients need, products can be reached :DIN75200,B1,B2,NFPA701		
Cd% ,Pb%,As%,Ba%, Cr%,Hg%,Se%	If the clients need, we can reach EN71-3: Cd% <100ppm,Pb% <90ppm,As% <25ppm,Ba% <1000ppm Cr% <60ppm,Hg% <60ppm,Se% <500ppm		