



Technical Data Sheet: CX13 PETG SERIES 3D PRINTING FILAMENT

BASE RESIN: EASTMAN EASTAR PETG Copolyester

Physical Properties	Standard	Unit	Typical Value
Specific Gravity - Density	ASTM D792	g/cc	1.27
Melt Density @200°C	ASTM D1238	g/cm ³	1.19
UL Flammability Class. @1.14mm	UL 94	N/A	94HB

Mechanical Properties	Standard	Unit	Typical Value
Tensile Yield Strength	ASTM D638	MPa	50
Tensile Modulus	ASTM D638	MPa	2100
Tensile Elongation	ASTM D638	%	130
Flexural Stress	ISO 178	MPa	68
Notched Izod Impact	ASTM D256	J/m	100
Shrinkage Rate < 1%	ASTM D955	mm/mm	.0004

Thermal Properties	Standard	Unit	Typical Value
Glass Transition Temperature (Tg)	DSC	°C	80
Heat Distortion Temp @ 0.45MPa	ASTM D648	°C	70
Decomposition Temperature	ASTM 3418	°C	280

SPECIFICATIONS				
Filament Size:	1.75mm	0.0689 in	2.85mm	0.1122 in
MIN Diameter:	1.72mm	0.0677 in	2.79mm	0.1098 in
MAX Diameter:	1.78mm	0.0701 in	2.91mm	0.1146 in
Tolerance				
Standard Dev.	+/- .03mm	+/- 0.0012 in	+/- .06mm	+/- 0.0024 in
Ovality				

CERTIFICATIONS
Meets ISO 10992 and/or USP Class VI biocompatibility requirements; Food Contact Status compliant
Chemical Resistance per Eastman pub. TR-145
CRADLE TO CRADLE CERTIFIED Silver
UL Yellow Card E118289 – 101981969
GREENGUARD INDOOR AIR QUALITY CERTIFIED
Not suited for continuous outdoor exposure

Printed Specimen Conditions
Printer: Open Source FDM/FFF
Nozzle: 0.4mm
Layer Height: 0.25mm
Infill: 100%, +/-45°
Extrusion Temp: 250°C
Bed Temp: 80°C
Specimen Orientation: XY Flat
Unannealed

Disclaimer: The technical data contained on this data sheet is furnished without charge or obligation and accepted at the recipient's sole risk. This data should not be used to establish specifications limits or used alone as the basis of design. The data provided is not intended to substitute any testing that may be required to determine fitness for any specific use.