

Product Description

Infinity Seam Dripless is a non-sag methacrylate adhesive designed for the structural bonding of various substrates, including acrylic, polyester, alloy, polycarbonate, fiberglass, and various plastics (no low energy surfaces). Combined at a ratio of 10:1, Infinity Seam Dripless has a working time of 8 to 12 minutes and achieves nearly 90 percent of its ultimate strength in 20 to 25 minutes at room temperature curing. Infinity Seam Dripless provides high strength bonds to the above reference surfaces with generally no preparation effort and is totally dripless. There's no mess on the floor, tools, or clamps. Infinity Seam Dripless adhesives are UV stable and will not yellow over time.

Company Information:

Infinity Bond Adhesives
7667 Cahill Rd, STE 100
Edina, MN 55439
Phone: (844) 366-7272
Website: www.infinitybond.com

Characteristics

Work Time	8 to 12 minutes (at 75°F/ 24°C)
Fixture Time	20 to 25 minutes (at 75°F/ 24°C)
Can Be Moved In	30 minutes
Operating Temperature	65°F to 85°F (18°C to 30°C)
Gap Filling	.50 inches
Mixed Density	8.1 lbs/gal (.96 g/cc)
Flash Point	51°F (11°C) – See SDS

Chemical Resistance

Excellent Resistance to:

- Hydrocarbons
- Acids and Bases
- Vinegar
- Wine and Condiments
- Most Household Foods

Susceptible to:

- Polar Solvents
- Super Strong Acids and Bases

Physical Properties

Uncured	Resin	Activator
• Viscosity (cps)	60,000-100,000	20,000-50,000
• Color	Various	Clear
• Density (lbs/gal)	8.2	8.0
• Mix Ratio (wt or vol)	10.0	1.0
• Mixer Recommendation Cartridge (200/400ml): MFQX 08-24T – Square 24 element Green/Orange Mix Tips (10:1)		

Mechanical Properties

Tensile Strength	Substrate	Results	Failure Type
• Strength, psi	Fiberglass Surfaces	2,500+	Substrate
• Strength, psi	Acrylic Sheeting	1,000+	Substrate
• Strength, psi	Polycarbonate Sheeting	1,000+	Substrate

Handling & Application

Infinity Seam Dripless (Part A) and activator (Part B) are flammable. Contents include Methacrylate ester and acids. Keep containers closed after use. Wear gloves and safety glasses to avoid skin and eye contact. Wash with soap and water after skin contact. In case of eye contact, flush with water for 15 minutes and get medical attention. Harmful if swallowed. Keep out of the reach of children. Keep away from heat, sparks, and open flames. Do not smoke cigarettes or anything else while handling or near the product. Refer to the Infinity Seam Safety Data Sheet for more complete safety instruction. To assure maximum bond strength, surfaces must be mated together within the specified working time, and all clamps affixed within that time. Use sufficient material to ensure that the joint is completely filled when parts are mated and clamped. Avoid over clamping parts, which may cause a dry joint or a joint starved of adhesive. All adhesive application, part positioning, fixturing, and clamping should occur before the working time of the adhesive has expired. After the indicated working time, parts must remain undisturbed until the fixture time is completed. Components bonded, adhesive, and shop temperature can have a significant effect on the work and fixture time of the adhesive. Application of Infinity Seam Dripless adhesive at temperatures between 65°F and 85°F (18°C and 30°C) will ensure proper cure. Temperatures below 65°F (18°C) will slow cure and fixture speed. Infinity Seam Dripless adhesives will still react, but will take longer. Temperatures above 85°F (18°C and 30°C) will increase cure and fixture speeds, and there's a risk that the adhesive will be hardened or too thick to bond materials. The viscosities of Infinity Seam Dripless adhesives are affected by temperature.

NOTE: Because of the curing features of Infinity Seam Dripless adhesives, large amounts of heat are generated when large masses of material are mixed at one time. The heat generated by the exotherm resulting from mixing large amounts of adhesive can result in a boiling of the monomer in the adhesive (methyl methacrylate), resulting in the release of trapped air, steam and volatile gasses. To prevent this, use only enough material as needed for use within the working time for the product, and confine the gap or spread out the material to no more than 1.00 inches.

Handling & Application

The shelf life of Infinity Seam Dripless is twelve (12) months from the date of manufacture based upon continuous storage at room temperature (77°F or 25°C). Storage of Infinity Seam Dripless adhesives in refrigerated compartments will extend the shelf life even more. Do not store Infinity Seam Dripless adhesive or any other adhesives in a refrigerator which has food or lunch products in them. Be sure to bring Infinity Seam Dripless adhesives to room temperature for 24 hours before use, otherwise longer cure and fixture times may be expected. Long-term storage at temperatures above room temperature will shorten the shelf life of Infinity Seam Dripless adhesives considerably. Storage at temperatures above 100°F or 38°C could shorten the shelf life to less than one month. Infinity Seam Dripless adhesives contain no water, so freezing of the adhesive for short periods is permissible, but is not encouraged.

Note to Customers

NOTE: Information contained herein is based on tests we believe to be reliable and accurate. It is offered in good faith for the benefit of the consumer. The Company shall not be liable for any injury, loss, or damage in the use or handling of its chemical products since conditions and use are beyond our control. In every case, we urge and recommend the user conduct tests to determine to their own satisfaction that the product is of acceptable quality and suitability for their particular purpose under their own operating conditions. Statements concerning possible use of our products are not intended as recommendations to use our products in the infringement of any patent, or for any particular purpose or application. These products are intended for industrial use only.