

## Product Description

Infinity Seam Standard is a flowable methacrylate adhesive designed for the structural bonding of various substrates, including acrylic, polyester, alloy, polycarbonate, fiberglass, and various plastics (not low energy surfaces). Combined at a ratio of 10:1, Infinity Seam Standard has a working time of 8 to 12 minutes and achieves nearly 90 percent of its ultimate strength in 20 to 25 minutes at room temperature curing. Infinity Seam Standard provides high strength bonds to the above reference surfaces with generally no preparation effort. Infinity Seam Standard adhesives are UV stable, and will not yellow over time.

## Company Information:

**Infinity Bond Adhesives**  
7667 Cahill Rd, STE 100  
Edina, MN 55439  
Phone: (844) 366-7272  
Website: [www.infinitybond.com](http://www.infinitybond.com)

## Characteristics

Work Time	8 to 12 minutes (at 75°F/ 24°C)
Fixture Time	20 to 25 minutes (at 75°F/ 24°C)
Can Be Moved In	30 minutes
Operating Temperature	65°F to 85°F (18°C to 30°C)
Gap Filling	.250 inches
Mixed Density	8.1 lbs/gal (.96 g/cc)
Flash Point	51°F (11°C) – See SDS

## Chemical Resistance

### Excellent Resistance to:

- Hydrocarbons
- Acids and Bases
- Vinegar
- Wine and Condiments
- Most Household Foods

### Susceptible to:

- Polar Solvents
- Super Strong Acids and Bases

## Physical Properties

### Uncured

- Viscosity (cps)
- Color
- Density (lbs/gal)
- Mix Ratio (wt or vol)
- Mixer Recommendation Cartridge (200/400ml): MFQX 08-24T – Square 24 element White/Green Mix Tips (10:1):

### Resin

- 30,000-60,000
- Various
- 8.2
- 1.0

### Activator

- 20,000-50,000
- Clear
- 8.0
- 1.0

## Mechanical Properties

Tensile Strength	Substrate	Results	Failure Type
• Strength, psi	Fiberglass Surfaces	2,500+	Substrate
• Strength, psi	Acrylic Sheeting	1,000+	Substrate
• Strength, psi	Polycarbonate Sheeting	1,000+	Substrate

## Handling & Application

Infinity Seam Standard resin (Part A) and activator (Part B) are flammable. Contents include Methacrylate ester and acids. Keep containers closed after use. Wear gloves and safety glasses to avoid skin and eye contact. Wash with soap and water after skin contact. In case of eye contact, flush with water for 15 minutes and get medical attention. Harmful if swallowed. Keep out of the reach of children. Keep away from heat, sparks, and open flames. Do not smoke cigarettes or anything else while handling or near the product. Refer to the Infinity Seam Standard Safety Data Sheet for more complete safety instruction. To assure maximum bond strength, surfaces must be mated together within the specified working time, and all clamps affixed within that time. Use sufficient material to ensure that the joint is completely filled when parts are mated and clamped. Avoid over clamping parts, which may cause a dry joint or a joint starved of adhesive. All adhesive application, part positioning, fixturing, and clamping should occur before the working time of the adhesive has expired. After the indicated working time, parts must remain undisturbed until the fixture time is completed. Components bonded, adhesive, and shop temperature can have a significant effect on the work and fixture time of the adhesive. Application of Infinity Seam Standard adhesive at temperatures between 65°F and 85°F (18°C and 30°C) will ensure proper cure. Temperatures below 65°F (18°C) will slow cure and fixture speed. Infinity Sea Standard adhesives will still react, but will take longer. Temperatures above 85°F (18°C and 30°C) will increase cure and fixture speeds, and there's a risk that the adhesive will be hardened or too thick to bond materials. The viscosities of Infinity Seam Standard adhesives are affected by temperature.

**NOTE:** Because of the curing features of Infinity Seam Standard adhesives, large amounts of heat are generated when large masses of material are mixed at one time. The heat generated by the exotherm resulting from mixing large amounts of adhesive can result in a boiling of the monomer in the adhesive (methyl methacrylate), resulting in the release of trapped air, steam and volatile gasses. To prevent this, use only enough material as needed for use within the working time for the product, and confine the gap or spread out the material to no more than .50 inches.

## Handling & Application

The shelf life of Infinity Seam Standard is twelve (12) months from the date of manufacture based upon continuous storage at room temperature (77°F or 25°C). Storage of Infinity Seam Standard adhesives in refrigerated compartments will extend the shelf life even more. Do not store Infinity Seam Standard adhesive or any other adhesives in a refrigerator which has food or lunch products in them. Be sure to bring Infinity Seam Standard adhesives to room temperature for 24 hours before use, otherwise longer cure and fixture times may be expected. Long-term storage at temperatures above room temperature will shorten the shelf life of Infinity Seam Standard adhesives considerably. Storage at temperatures above 100°F or 38°C could shorten the shelf life to less than one month. Infinity Seam Standard adhesives contain no water, so freezing of the adhesive for short periods is permissible, but is not encouraged.

**Note to Customers**

NOTE: Information contained herein is based on tests we believe to be reliable and accurate. It is offered in good faith for the benefit of the consumer. The Company shall not be liable for any injury, loss, or damage in the use or handling of its chemical products since conditions and use are beyond our control. In every case, we urge and recommend the user conduct tests to determine to their own satisfaction that the product is of acceptable quality and suitability for their particular purpose under their own operating conditions. Statements concerning possible use of our products are not intended as recommendations to use our products in the infringement of any patent, or for any particular purpose or application. These products are intended for industrial use only.