

Australian Wool Testing Authority Ltd - trading as AWTA Product Testing A.B.N 43 006 014 106

1st Floor, 191 Racecourse Road, Flemington, Victoria 3031

P.O Box 240, North Melbourne, Victoria 3051

Phone (03) 9371 2400

Group Number Assessment

(In accordance with AS 5637.1-2015


This is to confirm that the product as described below has been tested by AWTA Product Testing .

Testing was performed in accordance with AS/NZS 3837-1998 Method of test for heat and smoke release rates for materials and products using an oxygen consumption calorimeter.

As per AS 5637.1 Clause 9(n) it was valid to test this particular material / system in the cone calorimeter for the assignment of a NCC Group Number.

Test Sponsor :	Braeside Mills Operations P/L, T/A as Armstrong Flooring	Test Number	:	23-002009
	29-39 Mills Road	Issue Date	:	1/06/2023
	Braeside VIC 3195	Print Date	:	1/06/2023

Sponsor Product :	Clients Ref : "Accessories" Extruded PVC flooring and walling accessories
	Colour : Grey End Use : Flooring and walling accessories
	Nominal Composition : PVC compound
	Nominal Mass per Unit Area/Density : 2300g/m2
	Nominal Thickness : 1.40mm



The message/document(s) contained in this electronic attachment is intended for the party to which it is addressed and may contain confidential information or be subject to professional privilege. It's transmission is not intended to place the contents into the public domain.

If you have received this transmission in error, it's disclosure or copying is prohibited. Please contact us by collect call so that arrangements can be made at our expense to rectify the error.



Australian Wool Testing Authority Ltd - trading as AWTA Product Testing A.B.N 43 006 014 106

1st Floor, 191 Racecourse Road, Flemington, Victoria 3031

P.O Box 240, North Melbourne, Victoria 3051

Phone (03) 9371 2400

Group Number Assessment

(In accordance with AS 5637.1-2015

This is to confirm that the product as described below has been tested by AWTA Product Testing .

Testing was performed in accordance with AS/NZS 3837-1998 Method of test for heat and smoke release rates for materials and products using an oxygen consumption calorimeter.

As per AS 5637.1 Clause 9(n) it was valid to test this particular material / system in the cone calorimeter for the assignment of a NCC Group Number.

Test Sponsor :	Braeside Mills Operations P/L, T/A as Armstrong Flooring 29-39 Mills Road		Test Number Issue Date	:	23-002009 1/06/2023
	Braeside VIC 3195		Print Date	:	1/06/2023
Product Group N	umber Classification :	2			
Average Specific	Extinction Area :	211.7	m²/kg		

Allowed d.

Fiona McDonald Testing Technologist

The message/document(s) contained in this electronic attachment is intended for the party to which it is addressed and may contain confidential information or be subject to professional privilege. It's transmission is not intended to place the contents into the public domain.

If you have received this transmission in error, it's disclosure or copying is prohibited. Please contact us by collect call so that arrangements can be made at our expense to rectify the error.