



ST Color Zirconia Block

- Pr-shaded technics
- Uniform color
- Without post dyeing process
- Suitable for full contour crown, bridge and anterior

Indications



Physical Characteristics

Sintered density	6.07±0.03g/cm ³
Bending Strength	≥1100MPa(Av.)
Transmittance	43%
Hardness	1200HV
Sintering temperature	Recommend 1530°C