SILFAB NTC

SIL-440 QD





♠ NEXT-GENERATION N-TYPE CELL TECHNOLOGY

- Improved Shade Tolerance
- Improved Low-Light Performance
 Reduced Degradation Rate
- Increased Performance in High Temperatures
- Enhanced Durability
- 25-Year Product Warranty/ 30-Year Performance Warranty





SILFABSOLAR.COM









ELECTRICAL SPECIFICATIONS		440		
Test Conditions		STC	NOCT	
Module Power (Pmax)	Wp	440	328.0	
Maximum power voltage (Vpmax)	V	33.41	31.17	
Maximum power current (Ipmax)	A	13.17	10.52	
Open circuit voltage (Voc)	V	38.97	36.64	
Short circuit current (Isc)	А	14.22	11.44	
Module efficiency	%	22.6%		
Maximum system voltage (VDC)	V	1000		
Series fuse rating	A	25		
Power Tolerance	Wp	0 to +10		


 $Measurement\ conditions:\ STC\ 1000\ W/m^2\bullet AM\ 1.5\bullet Temperature\ 25\ ^\circ C\bullet NOCT\ 800\ W/m^2\bullet AM\ 1.5\bullet Measurement\ uncertainty \le 3\%$ $Sun simulator calibration \ reference\ modules\ from\ Fraunhofer\ Institute.\ Electrical\ characteristics\ may\ vary\ by\ \pm 5\%\ and\ power\ by\ 0\ to\ + 10\ W.$

MECHANICAL PROPERTIES / COMPONENTS	METRIC	IMPERIAL	
Module weight	21 kg ± 0.2 kg	46.3 lbs ± 0.4 lbs	
Dimensions (H x L x D)	1721 mm x 1133 mm x 35 mm	67.8 in x 44.6 in x 1.37 in	
Maximum surface load (wind/snow)*	4000 Pa rear load / 5400 Pa front load	83.5 lb/ft² rear load / 112.8 lb/ft² front load	
Hail impact resistance	ø 25 mm at 83 km/h	ø 1 in at 51.6 mph	
Cells	108 Half cells - N-Type Silicon solar cell 182 mm x 91 mm	108 Half cells - N-Type Silicon solar cell 7.16 in x 3.58 in	
Glass	3.2 mm high transmittance, tempered, antireflective coating	0.126 in high transmittance, tempered, antireflective coating	
Cables and connectors (refer to installation manual)	1350 mm, ø 5.7 mm, MC4 from Staubli	53.1 in, ø 0.22 in (12 AWG), MC4 from Staubli	
Backsheet	High durability, superior hydrolysis and UV resistance, multi-layer dielectric film, fluorine-free PV backsheet		
Frame	Anodized aluminum (Black)		
Junction Box	UL 3730 Certified, IEC 62790 Certified, IP68 rated, 3 diodes		

TEMPERATURE RATINGS		WARRANTIES		
Temperature Coefficient Isc	0.04 %/°C	Module product workmanship warranty	25 years**	
Temperature Coefficient Voc	-0.24 %/°C	Linear power performance guarantee	30 years	
Temperature Coefficient Pmax	-0.29 %/°C		≥ 98% end 1st yr ≥ 94.7% end 12th yr	
NOCT (± 2 °C)	45 °C		≥ 94.7% end 12th yr ≥ 90.8% end 25th yr	
Operating temperature	-40/+85 °C		≥ 89.3% end 30th yr	

	CERTIFICATIONS		SHIPPING SPECS	
	Product	UL 61215, UL 61730, CSA C22.2#61730, IEC 61215, IEC 61730, IEC 61701 (Salt Mist Corrosion), IEC 62716 (Ammonia Corrosion), CEC Listed, UL Fire Rating: Type 2	Modules Per Pallet:	26 or 26 (California)
			Pallets Per Truck	32 or 30 (California)
	Factory	ISO9001:2015	Modules Per Truck	832 or 780 (California)

- **A** Warning. Read the Safety and Installation Manual for mounting specifications and before handling, installing and operating modules.
- 12 year extendable to 25 years subject to registration and conditions outlined under "Warranty" at silfabsolar.com. PAN files generated from 3rd party performance data are available for download at: silfabsolar.com/downloads.



SILFAB SOLAR INC.

1770 Port Drive

Burlington WA 98233 USA

T +1 360.569.4733

info@silfabsolar.com

SILFABSOLAR.COM

7149 Logistics Lane

Fort Mill SC 29715 USA

T +1 839.400.4338

240 Courtneypark Drive East Mississauga ON L5T 2Y3 Canada

T +1 905.255.2501

F +1 905.696.0267

Sales & Customer Support

T +1.833.998.6642

Silfab - SIL-440-QD-20250702

No reproduction of any kind is allowed without permission. Data and information is subject to modifications without notice. © Silfab Solar lnc., 2022. Silfab Solar* is a registered trademark of Silfab Solar inc.