

Product Information

INFINAM® RG 7100 L

HIGH IMPACT STRENGTH BLACK PHOTOPOLYMER FOR ADDITIVE MANUFACTURING



INFINAM® RG 7100 L resin is a black colored liquid photopolymer formulation, which is easy to process (1-part system). The fully cured material exhibits excellent mechanical properties (high impact strength).

Directions for use

INFINAM® RG 7100 L resin is a light-sensitive product protected by its original packaging. Exposure of the liquid formulation to daylight or UV light should be minimized or avoided at all during storage and handling to ensure consistent print quality. Special light sources shall be used instead. Store product in a dry location with optimum storage temperature of 10–30 °C. Storage beyond this recommended temperature range can adversely affect both print and product properties.

It is recommended to shake **INFINAM® RG 7100 L** resin well before use. Degassing can be carried out before any print process. It is advisable not to store the unused resin in the vat, especially for prolonged period of usage. If the resin is left in the vat after printing, thoroughly mix and agitate the resin in the vat prior to any print processes. Do not return used resin from the vat back into the original **INFINAM® RG 7100 L** container.

Recommended print settings

INFINAM® RG 7100 L is designed to print on bottom-up digital light processing (DLP) machines. When printing with a light intensity of 11 mW/cm² at 405 nm, the recommended layer exposure time for 100 µm thick layers is 4 s, with a base layer exposure time of 7 s. Working curve data for 405 nm wavelength and 11 mW/cm² intensity: Critical exposure energy $E_c = 7\text{--}10 \text{ mJ/cm}^2$ and Depth of penetration $D_p = 170\text{--}250 \text{ µm}$. Setting printing temperature to 35–38 °C is highly recommended.

Recommended washing procedure

It is recommended to wash printed parts with isopropanol (IPA) to remove uncured resin. Rinse 2 to 3 times, each rinse for 2–5 minutes. Rinse until excess resin have been completely removed. After the IPA washing, allow IPA to drip from the printed parts for 5 to 10 minutes, afterwards, allow parts to dry for at least 30 minutes after washing to allow IPA to fully evaporate before the next post-curing process. When support structures are used, they should be removed before post-curing.

Recommended post-curing procedure

After washing, the parts should be submitted to ultraviolet (UV) light (intensity at ca. 5 mW/cm²) for 120 min at 80 °C, followed by 180 min at 80 °C without UV light.

Mechanical testing measurements

The mechanical values reported in this document were obtained on specimens printed with a DLP printer at 405 nm (11 mW/cm², XY or XZ print with 4 s layer exposure time, 100 µm thick layers). Tensile bars were tested following ASTM D638, Type V, 10 mm/min using an automated extensometer. Specimens are notched using a manual notching machine.

Statement on reported mechanical and thermal properties

The mechanical and thermal values reported in this document derived from printing various parts with one specific bottom-up DLP machine and following the above-mentioned procedures. Those values reflect an approximation of the mean value of a range of values and are intended for reference and comparison purposes only.

Mechanical Properties	Value	Unit	Test Standard
Tensile Modulus	1450	MPa	ASTM D638
Ultimate Tensile Strength	51	MPa	ASTM D638
Elongation at Break	48	%	ASTM D638
Flexural Modulus	1370	MPa	ASTM D790
Flexural Stress at 5% Strain	55	MPa	ASTM D790
Izod Notched Impact	80	J/m	ASTM D256

Thermal Properties	Value	Unit	Test Standard
Heat Deflection Temperature, 0.455 MPa/66 psi	66	°C	ASTM D648
Heat Deflection Temperature, 1.82 MPa/264 psi	52	°C	ASTM D648
Glass Transition Temperature (tanδ)	105	°C	ASTM D4065

Physical Properties	Value	Unit	Test Standard
Liquid Density, 25 °C	1.07	g/cm ³	ASTM D4052
Liquid Viscosity, 25 °C / 1 Hz	4,870	mPa.s	ASTM D4287
Shore D Hardness	81	-	ASTM D2240
Water absorption (24 h)	1.1	%	ASTM D570
Water absorption (48 h)	1.9	%	ASTM D570
Water absorption (72 h)	2.8	%	ASTM D570

This information and any recommendations, technical or otherwise, are presented in good faith and believed to be correct as of the date prepared. Recipients of this information and recommendations must make their own determination as to its suitability for their purposes. In no event shall Evonik assume liability for damages or losses of any kind or nature that result from the use of or reliance upon this information and recommendations. EVONIK EXPRESSLY DISCLAIMS ANY REPRESENTATIONS AND WARRANTIES OF ANY KIND, WHETHER EXPRESS OR IMPLIED, AS TO THE ACCURACY, COMPLETENESS, NON-INFRINGEMENT, MERCHANTABILITY AND/OR FITNESS FOR A PARTICULAR PURPOSE (EVEN IF EVONIK IS AWARE OF SUCH PURPOSE) WITH RESPECT TO ANY INFORMATION AND RECOMMENDATIONS PROVIDED. Reference to any trade names used by other companies is neither a recommendation nor an endorsement of the corresponding product and does not imply that similar products could not be used. Evonik reserves the right to make any changes to the information and/or recommendations at any time, without prior or subsequent notice.

INFINAM® is registered trademark of Evonik Industries AG or one of its subsidiaries

Evonik Operations GmbH
Smart Materials
High Performance Polymers
 45772 Marl / Germany

Tel: +49 2365 49 - 9227
 evonik-hp@evonik.com