# **Material Safety & Technical Data Sheet**

## GA-380 Black High Performance Rubber Toughened Cyanoacrylate Adhesive

## GLOBAL ADHESIVES, LLC

1. Product Identification

Product Name #GA-380

Product High Performance Low Viscosity Black Cyanoacrylate Adhesives

2. Composition

Ingredients	CAS#	<u>WT%</u>
Ethyl Cyanoacrylate	7085-85-0	90-99
Poly Methyl Methacrylate	9011-14-7	1-10
Proprietary Additive	Proprietary	4-6
Hydroquinone	12-31-9	.1-1.0

**Ingredients That Have Exposure Limits** 

**Exposure Limits (TWA) ACGIH OSHA** Other Ingredients (TLV) (PEL) Ethyl Cyanoacrylate 0.2 ppm TWA None None 2mg/m3TWA Hydroqinone 2mg/m (TWA 2mg/m3TWA 4mg/m3STEL

**Exposure Limits (STEL)** 

Ethyl Cyanoacrylate (4ppm) (4ppm) (18mg.m3) (16mg/m3)

3. Hazard Identification

**Toxicity** Skin contact may cause burns. Bonds skin rapidly.

Skin and eye Irritant

Estimated oral LD more than 5,000 mg/kg. Estimated dermal LD 50 more than 2,000 mg/kg.

Primary Routes of Entry None Know

Symptoms of Exposure Vapor is irritating to the mucous membrane when above TLV. Prolonged and

repeated overexposure to vapors may produce allergic reactions with asthma like

symptoms in sensitive individuals.

Existing Conditions Aggravated by Exposure None Known

**Target Organs and Other Health Effects** 

Carcinogens NTP **OSHA** IARC Methyl Cyanoacrylate Allergen, irritant, respiratory No No No Poly (methyl Methacrylate) No N/A No Hydroquinone ACGIH animal carcinogen, No N/A No

Blood, bone marrow, central Nervous system, eye, immune System, irritant, liver, skin, Mutagen, thyroid.

#### 4. First Aid Measures and Personal Protection

Note: See supplemental page or emergency procedures and additional First Aid information

**Ingestion** Ingestion is not likely.

**Inhalation** Remove to fresh air. If symptoms persist, obtain medical attention.

Skin contact Soak in warm water.

Eye contact Flush with water

Personnel protection

Eye Chemical safety glasses or goggles.

Skin Polyethylene gloves and/or aprons. DO NOT use cotton/cloth type gloves

Ventilation Positive draft exhaust ventilation should be provided to maintain vapor concentration levels below TLV.

5. Fire Fighting Measures

Flash Point 160-200° F (Method TCC)

**Extinguishing Agents** Carbon dioxide, foam, dry chemical.

**Special Fire Fighting** 

Procedures Not available

**Hazardous Products Formed by** 

Fire or Thermal Decomp Irritating organic vapors

Unusual Fire or Explosion Hazards None

## GLOBAL ADHESIVES, LLC

### **#GA-380** Page 2

#### 5. Fire Fighting Measures (cont.)

**Explosive Limits** 

(% by volume in air) Lower Not available (% by volume in air) Upper Not available

#### **Accidental Release Measures**

If a spill or leak occurs flood area with water to polymerize (cure) the material. Soak up with an inert absorbent.

#### 7. Handling and Storage

Storage Store below 72°F

Handling Avoid contact with skin and eyes. Avoid breathing vapors.

#### **Physical and Chemical Properties**

**Appearance** Black liquid Odor Sharp, irritating **Boiling Point** More than 300°F Solubility in Water Polymerized **Specific Gravity** 1.05 @ 75°F

Vapor Pressure Less than .2mm @ 75°F

Vapor Density

VOC 87.1%; 914.55 g/l (EPA Method 24)

#### 9. Stability and Reactivity

Stability Stable **Hazardous Polymerization** Will not occur

Incompatibility Polymerized by contact with water, alcohol, amines, alkalies

**Conditions to Avoid Hazardous Decomposition Products** (Non-thermal); None

#### 10. Toxicological Information

Refer to number 3.

#### 11. Ecological Information

No data available.

#### 12. <u>Disposal Considerations</u>

Recommended methods of disposal Polymerize as indicated in number 6. Incinerate following EPA and local regulations.

EPA Hazardous waster number: NH-Not a RCRA Hazardous Waste Material.

#### 13. Transportation information

#### DOT (49CFR 172) Domestic Ground Transport

Unrestricted (not more than 450 liters) Combustible liquids, n.o.s.(Cyanoacrylates)(more than 450 liters) **Proper Shipping Name** 

**Hazard Class or Division** Unrestricted (not more than 450 liters)

**Identification Number** None (not more than one pint)

NA 1993 (more than 450 liters)

**Marine Pollutant** None

IATA

**Proper Shipping Name** Unrestricted (not more than one pint)

Aviation regulated liquid, n.o.s., (Cyanoacrylate)(more than one pint)

Class or Division Unrestricted (not more than one pint) Class 9 (more than one pint)

**UN or ID Number** None (not more than one pint)

UN 3334 (more than one pint

#### 14. Regulatory Information

**CA Proposition 65:** No Prop 65 chemicals known to be present

We believe the information contained herein is current and accurate as of this date of this Material Safety Data Sheet. Since the use of this information and these opinions and the conditions of use of this product are not under the control of Global Adhesives, LLC. Or it's agents or distributors; it is the user's obligation to determine the conditions of safe use of this product. The buyer should conduct its own test of this product before use to determine proper preparation technique and suitability for proposed application. Global Adhesives, LLC. Warrants that the product conforms with Global Adhesives, LLC. Written Specifications, and id free from defects and disclaims all other warranties, expressed or implied and is not responsible for loss claim of damage resulting from the use of it's products.

#### GA-380 TECHNICAL DATA SHEET

## **GA-380** Page 3

#### **LIQUID PROPERTIES**

Ester Base Ethyl-2-cyanoacrylate

Appearance Black Flashpoint >81°C Density 1.05

Shelf Life 12 months, unopened

Viscosity (Brookfield) @ 25°C (Spindle 1, 20rpm) 300-400 cP

#### **POLYMER PROPERTIES**

Appearance Black Softening Point c.  $130^{\circ}$ C Refractive Index,  $n_D^{20}$  1.45 Full Cure Time 24 hours

Solubility DMF, acetonitrile, acetone

#### **CURED PERFORMANCE**

#### **Cure Speed**

Balsa / Balsa <10 seconds Oak / Oak 90-180 seconds <10 seconds Nitrile / Nitrile Neoprene / Neoprene <10 seconds EPDM / EPDM <10 seconds Steel / Steel 10-20 seconds PVC / PVC 3-10 seconds Polycarbonate / Polycarbonate 10-40 seconds

Sheer Strength

Grit Blasted Steel >15 N/mm²
Etched Aluminum >11 N/mm²
Nitrile Rubber >10 N/mm²
Polycarbonate >12 N/mm²

Tensile Strength

Grit Blasted Steel >18 N/mm²
Nitrile Rubber >5 N/mm²
Neoprene Rubber >5 N/mm²
EPDM Rubber >2.5 N/mm²

#### PRODUCT STORAGE

Global Adhesives, LLC. cyanoacrylates should ideally be stored in original sealed containers until used. Containers should be stored between 10C and 22C; avoid exposure to strong light and heat sources. Refrigeration prolongs shelf life.

#### DISCLAIMER

The data contained within the Technical Data Sheet are furnished for information only and are believed to be reliable at the time of issue. We cannot assume responsibility for results obtained by others over whose methods we have no control. It is the responsibility of the user to determine the products suitability for use. Global Adhesives, LLC. and its distributors and agents accept no liability arising out of the use of this information of the products described herein.