

PARADOR

Laminate Basic 600V

Product quality		Tolerances (EN 13329)	
Formats	1285 x 243 x 8 mm	Squareness of the elements (≤ 0.50 mm)	$\leq 0,10$ mm
Packaging	Pack: 7 elements / 2,186 m ² / 15,46 kg	Determination of Linearity (≤ 0.30 mm)	$\leq 0,10$ mm/m
	Pallet: 42 packs / 91,80 m ² / 665 kg	Block alignment	± 2 mm
Guarantee (according Parador guarantee conditions)	Domestic area	Surface flushness	(average ≤ 0.15 mm)
	Commercial area		(max. ≤ 0.15 mm)
Notes	15 years 5 years - not suitable for all-over adhesion - cleaning and maintenance see instructions - technical changes reserved	Opening between installed elements	(average ≤ 0.15 mm)
			(max. ≤ 0.20 mm)
		Flatness of elements	fw, concave $\leq 0,15$ % fw, convex $\leq 0,20$ % fl, concave $\leq 0,50$ % fl, convex $\leq 1,00$ %



Classification		Test method	Rating
	Nutzungsklasse 23 Stark beanspruchter privater Wohnbereich	EN 13329	Living room, hall, kitchen, home office
	Nutzungsklasse 32 Mittelstark beanspruchter gewerblicher Bereich	EN 13329	Classrooms, small offices, shops
	Abrasion	EN 13329, Annex E	AC 4 (≥ 4.000 rev.)
	Impact resistance (small ball)	EN 17368	≥ 35 mm
	Impact resistance (big ball)	EN 13329, Annex H	≥ 750 mm
	Reaction to fire	EN 13501-1	Cfl s1
	Slip resistance	EN 13893 EN 14041	$\mu \geq 0,35$ DS
	Staining resistance	EN 438-2	Category 1+2: level 5 Category 3: level 4/5
	Cigarette resistance	EN 438-2	level 4
	Light fastness	EN ISO 4892-2	Grey scale: Stage ≥ 4
	Resistance to roller castor chairs	EN 425	Type W, no visible changes
	Thermal resistance Suitable for installation over underfloor heating when using an appropriate underlay and moisture barrier.	EN 12664	0,048 m ² *K/W
	Moving a furniture leg	EN ISO 16581	Type 0, no visible changes
	Indentation-residual	ISO 24343-1	$\leq 0,05$ mm
	Formaldehyde emission (E1 = 0.1 ppm)	EN 717-1	$\leq 0,05$ ppm
	Locking strength of mechanically assembled panels	ISO 24334	> 1 kN/m (long side) > 2 kN/m (short side)
	Acoustical - Impact noise reduction	ISO 717-2	14 dB (on Akustik-Protect 100)
	Dimensional stability	EN 13329, Annex C	$\leq 0,9$ mm
	Thickness swelling	ISO 24336 (≤ 18 %)	≤ 13 % 0
	Surface soundness	EN 13329, Annex D	$\geq 1,8$ N/mm ²
	Scratch resistance	EN 438	Level 4
	Slip resistance on an inclined plane	DIN 51130	Matt finish texture: R10 / Natural texture: R9
	Disposal		EAK-Code-number 20 01 38

Changed:	QMB Parador	File:	PA_TDS_Laminat_Basic-600_EN_20211101
Date:	01.01.2014	Latest update at:	www.parador.eu/service/catalogues-downloads/technical-data-sheets
Our technical data sheets are constantly updated and adapted to the latest technology. This version replaces all earlier versions and is valid from:			01.11.2021