

Silicone Plastique Specifications

Mix Ratio	1 to 1
Consistency	Putty
Durometer	40 ± 5 Shore A
Shelf Life	12 months
Tensile Strength	321 psi
Elongation	483%
Tear Strength	49 ppi
Work (Gel) Time	15-20 minutes
Demold Time	60-75 minutes
Temperature Range	-76°F to 392°F
Specific Gravity	1.38
Mix Color	Blue