



BG[®] Matt 3 mm

Properties	Units	Values	Test Method
Grammature	g/m ²	900	
Thickness	mm	3	
Density	Kg/m ³	300	
Elastic Modulus	KPa	884	Iso 178
Resistance to bending	KPa	12,07	Iso 178
Dimensional variation	%	max 0,5	
Surface finishing		MATT 5	
Corona-treatment level	Dynes/cm	> 42	Tested with specific liquids for treatment-level measurement

- » Resistance to water, to heavy weather conditions, to oils and chemical products
- » The product is 100% recyclable (mono-materic)
- » Available treatment: Anti-UV / Antistatic / Flame retardant

Tolerance	Weight	Thickness	Width	Length
	± 10%	± 5%	0/+ 1%	± 2%

The obtained results and the properties above refer to average values of lab tests on samples of our standard production. It is understood that entails no obligation and/or responsibility on Imballaggi Protettivi s.r.l. Customers should verify the suitability of the product for its specific end-use.



Imballaggi Protettivi srl

Direzione e stabilimento:

Via delle Industrie, 6 - 26815 - Massalengo (LO) - ITALY

Tel. +39.0371.78081 r.a. - Fax +39.0371.482831

info@imballaggiprotettivi.it - www.imballaggiprotettivi.it