



<sup>®</sup> Bubble  
Guard <sup>by I.P.</sup> matt

## BG<sup>®</sup> Matt 5 mm

Properties	Units	Values	Test Method
Grammature	g/m <sup>2</sup>	1600	
Thickness	mm	5	
Density	Kg/m <sup>3</sup>	320	
Elastic Modulus	Mpa	673	Iso 178
Resistance to bending	MPa	7,98	Iso 178
Dimensional variation	%	max 0,5	
Surface finishing		MATT 5	
Corona-treatment level	Dynes/cm	> 42	Tested with specific liquids for treatment-level measurement

- » Resistance to water, to heavy weather conditions, to oils and chemical products
- » The product is 100% recyclable (mono-materic)
- » Available treatment: Anti-UV / Antistatic / Flame retardant

Tolerance	Weight	Thickness	Width	Length
	± 10%	± 5%	0/+ 1%	± 2%

The obtained results and the properties above refer to average values of lab tests on samples of our standard production. It is understood that entails no obligation and/or responsibility on Imballaggi Protettivi s.r.l. Customers should verify the suitability of the product for its specific end-use.



### Imballaggi Protettivi srl

Direzione e stabilimento:

Via delle Industrie, 6 · 26815 - Massalengo (LO) · ITALY

Tel. +39.0371.78081 r.a. · Fax +39.0371.482831

info@imballaggiprotettivi.it · www.imballaggiprotettivi.it

