


Technical specification for the quality:

XQ2

	<p>XQ2 brings metallocene technology to landscape fibres</p> <ul style="list-style-type: none"> ✓ Fewer hexane (C6) copolymer side chains create even more crystalline (harder) fibres so the fibres stay upright longer ✓ The increased crystallinity makes it easier to retain fibre shape through the full production process of finer fibres
---	---

Yarn type	5,400 / 6 dTex PE monofilament S shape & 3,200 / 8 dTex PE monofilament curled
Yarn quality	Environmental friendly, free of lead and cadmium
Primary backing	100% PP, black, U.V. stabilized, weight 135 gr/m ²
Secondary backing	Black Latex compound with a base of SBR, with drainage holes, 836 gr/m ²
Water permeability	60 litre/min/m ²
Pile height	30 mm
Face Weight	1,580 gr/m ² +/- 10%
Total weight	2,551 gr/m ² +/- 10%
Tuft gauge	3/8 gauge
Stitches per 10 cm linear	24 +/- 1
Stitches per m ²	25,200 +/- 10%
Colour	Mix of light and dark green + green/beige thatch
UV stability	Meets DIN 53387 Standard (6000 hours)
Colour fastness	Xenon test: Bleu-scale > 7, Grey-scale > 4
Roll width	400 cm
Roll length	25m +/-
Sand Infill	6-8kg's p/m ²
Applications	Landscaping, Play, Multi