

Reinforced Acrylic over DensDeck

Part 1 – General

1.1 Summary

- A. This specification provides a guide on the installation of a reinforced acrylic over a DensDeck roof board.
- B. The suitability of the project should be determined by the contractor, and a representative of the owner. This system can be used as a new construction or restoration option over an existing substrate.
 - a. If used as a restoration solution, the existing system should be properly identified, and in sound condition.
- C. Elements of this specification may not apply to all situations. Such elements may be omitted if not applicable.

1.2 Related Work

- A. Repairs to the following should take place during the project:
 - a. Sheet Metal Defects
 - b. Surface Deviations
 - c. Flashing Defects
- B. A certified contractor should provide all labor, materials, equipment, and ancillary products required to install the acrylic coating restoration system.

1.3 Requirements

- A. Work must conform to applicable code regarding fire rating of existing roof system.
- B. All acrylics must be domestically produced. Products outside of the U.S. will not be accepted.
- C. Use of this product over cold storage or cryogenic facilities is not recommended. Acrylic has a moderate rate of water transmission, which could lead to the potential for accumulation of moisture in the insulation, deck, or both. Consult Marlin Coatings for recommendations on the use of a vapor barrier system on these types of structures.

1.4 Submittals

- A. Product Data: Submit specification, installation instructions, & general information for each acrylic product to be used.
- B. Safety Data Sheets
- C. Applicator should provide a Letter of Good Standing from the acrylic supplier.
- D. Sample Warranty
- E. Maintenance Instructions

1.5 Qualifications

- A. Installer:
 - a. Must be a Certified Contractor in good standing with Marlin Coatings.

- b. Must ensure all personnel working on the project have a full understanding of OSHA safety requirements.
- B. Supplier:
 - a. Primary products should be sourced from a single supplier, while secondary materials may be recommended by the primary supplier.

1.6 Delivery, Storage, & Handling

- A. All material should be stored in the original unopened container, in accordance with the recommendations by the supplier. Ensure to store materials in accordance with city, town, state, and/or federal regulatory agencies.
- B. Acrylic products should be stored between 40 - 90 degrees Fahrenheit, and indoors when possible. Do NOT let product freeze.
- C. Adequate ventilation and protective equipment should be provided to protect from hazardous fumes.
- D. Overspray protection should be used when spraying acrylic products.

1.7 Environmental Conditions

- A. Weather Limitations: Technical Data sheets for each acrylic product should be consulted to ensure proper installation during acceptable weather conditions.
 - a. Do not install acrylic below ambient temperatures of 50 degrees Fahrenheit, or if there is a chance that the temperature could fall below 32 degrees Fahrenheit within a 24-hour period after application.
 - b. Do not apply product if rain or dew is likely to occur before fully curing.

1.8 Warranty

- A. A labor & material warranty (10-, 15- or 20-year term) shall be provided to the building owner by Marlin Coatings.

Part 2 – Products

2.1 Materials

- A. Insulation board matching existing material.
- B. Roof Board - 5/8” DensDeck Prime or equivalent.
- C. Marlin Coatings: Polyester Reinforcing Fabric
- D. Marlin Coatings: Acrylic Flashing Grade
- E. Marlin Coatings: Acrylic One Pass
- F. Marlin Coatings: Acrylic Top Coat (to be used as basecoat, & intermediate coat)
- G. Marlin Coatings: High Tensile Acrylic (2 gallons per 100 square feet must be used as a top coat regardless of warranty term)

Acrylic Topcoat		
Property	Value	Test Method
Tensile Strength	270 (±22) psi	ASTM D-2370

Elongation	231 (± 22) %	ASTM D-2370
Solids by Volume	56 (± 3) %	ASTM D-1653
VOC	<50g/L	EPA Method 24
Reflectance	.86 initial	ASTM C-1549
Water Vapor Permeability	15 (± 4) perms	ASTM D-1653

H. Ancillary Products provided by Marlin Coatings:

- a. Walkway Coatings & Granules
- b. Skylight Coatings

Part 3 – Execution

3.1 Examination

- A. Identify and repair to any structural, deck, flashing, vents, ducts, gutters, penetrations, sheet metal or parapet wall components should be completed.
- B. Ensure all drains are in proper working condition.
- C. Verify that there are no areas of “ponding water” on the roof. Ponding water being defined as an area of standing water holding more than ½” of water, greater than 100sq.ft., 24 hours after rainfall. A roof system that allows standing water 48 hours after rainfall shall be considered unacceptable.

3.2 Preparation

- A. Clean the roof surface by first removing any heavy dirt deposits. Thoroughly power wash the areas to receive coating with a minimum of 2,000 psi of water pressure, removing dirt and loose particulates. Allow time for the roof to dry completely.
- B. Roof flashings and penetrations should be treated using Acrylic Flashing Grade, or Fleece Backed Butyl Reinforcing Tape and Acrylic Top Coat.
 - a. Apply 25 mils of coating over the Fleece Backed Butyl Reinforcing Tape to ensure complete encapsulation.
- C. Cracks & Seams should be treated using Acrylic Flashing Grade, extending at least 1” past each side of the crack. For cracks larger than ¼,” insert a backer rod into the crack and apply a thick coat of Acrylic Flashing Grade. Allow the Acrylic Flashing Grade to develop a thick “skin” before applying Acrylic Top Coat.
- D. Mechanically Fasten the roof board using the recommended fasteners and in accordance with the fastener pattern as specified by the manufacturer.

3.3 Acrylic Base, Fabric, Intermediate, and Top Coat Installation

- A. Before installation of Reinforcing Acrylic, verify that all previous applications of primer and acrylic have fully cured and that the area to be coated has a completely dry roof surface.

- B. Intermediate coat rates will vary depending on the warranty term requested. The following outlines the application rates relating to the warranty term.
 - For a 5 & 10-year warranty, intermediate coat should be applied at 1 gallon per 100 square feet.
 - For a 15-year warranty, intermediate coat should be applied at 1.25 gallon per 100 square feet.
 - For a 20-year warranty, intermediate coat should be applied at 2 gallon per 100 square feet.
- C. Using Acrylic Top Coat, install a base coat application at a rate of 2 gallons per 100 square feet. While the coating is still wet, embed 48" or 36" polyester fleece fabric into the basecoat. Polyester Fleece fabric should extend up walls at least 10". Use a nap roller to smooth out any wrinkles or fish mouths. Ensure each roll of fabric overlaps the previous roll by 3".
- D. Using Acrylic Top Coat, install the intermediate coat application at the rate described above corresponding to the warranty term desired.
- E. A final coat of High Tensile Acrylic should be applied to the entirety of the roof surface at a thickness of 2 gallons per 100 square feet.
- F. Vertical surfaces should be treated with care, as multiple coats will be required to avoid sagging. Avoid applying more than 12 wet mils in one coat on vertical surface.
- G. Equipment curbs must be coated up to the bottom of the metal cap of the unit and sealed underneath using Acrylic Top Coat or Acrylic Flashing Grade.
- H. Equipment placed on sleepers must be lifted so that the membrane underneath can be treated. Ensure to clean and prep these areas as done so with the field of the roof. An approved slip sheet should be used under the sleepers to protect the roof coating. Any areas that are not properly coated will be excluded from the warranty.

3.4 Walkways

- A. Walkway paths should be installed according to the direction of the building owner. A minimum of a 30" wide path should be used.
- B. Ensure to mask off the edges of the walkway during application to provide clean, straight edges.
- C. For areas requiring impact resistance, broadcast yellow walkway granules at a rate of 60lbs/square into 40 mil thickness of walkway coating. All other areas should receive walkway granules at a rate of 40lbs/square broadcast into 25 mil thickness of walkway coating.

3.5 Field Quality Control

- A. If a labor & material warranty is requested, then after the completion of the project a final inspection must be requested. There are to be no items on the roof that would inhibit a

complete and thorough inspection of the entirety of the roof coating project. Items that could inhibit the inspection process, but not limited to, are solar panels & decking systems.

- B. Any components of the roofing system that are not compliant to this specification must be removed, replaced, or corrected by the applicator.
- C. Before any foot traffic, there should be ample time for the roof to thoroughly dry after the completion of the project.
- D. Damage to the roof surface by other trades shall not be the responsibility of the certified contractor.