

AVIENT SPECIALTY INKS

PRODUCT INFORMATION BULLETIN



2570 INFINITE FX NUPUFF BASE

Avient™ Specialty Inks INFINITE FX NUPUFF is specifically designed to give a raised "puff" texture effect. NuPuff is extremely durable and formulated to resist overflow.

HIGHLIGHTS

- ▶ NUPUFF BASE | 2570
NUPUFF WHITE | 11000
NUPUFF BLACK | 19000
- ▶ Produces elevated "puff" surface with fantastic lift
- ▶ Tintable for infinite color combinations
- ▶ Excellent adhesion to fabrics, stretch properties, and wash durability
- ▶ Formulated to resist overflow

PRINTING TIPS

- ▶ Use consistent, high-tensioned screen mesh and sharp edged squeegees for best print results. Recommended mesh counts can vary depending on particle size
- ▶ Different effects may be achieved through the use of multiple passes, flash curing, thick screen stencils and overprinting with standard and specialty inks
- ▶ In multi-color printing, flash the puff prior to overprinting
- ▶ Best results when printed directly onto fabric
- ▶ Tintable with plastisol colorants. See Pigment Loading section for suggested starting tinting percentages. Reduce the amount of white colorant in the formula as specialty base will lighten the color
- ▶ NuPuff is formulated with overflow protection so the possibility of collapse of the expanded ink is greatly reduced
- ▶ If printing a large area, lightweight fabric may pucker. To alleviate puckering, print a mezzotint or dot pattern (an 80 percent solid)

COMPLIANCE

- ▶ Non-phthalate
- ▶ For individual compliance certifications and conformity statements, please visit www.avientspecialtyinks.com/services/compliance-support

PRECAUTIONS

The information above is given in good faith and does not release you from testing inks and fabrics to confirm suitability of substrate and application process to meet your customer standards and specifications

RECOMMENDED PARAMETERS



Fabric Types

100% cotton, cotton blends, some synthetics



Mesh

Count: 86-160 t/in (34-62 t/cm)
Tension: 25-35 n/cm²




Squeegee

Durometer: 60/90/60, 60-70
Profile: Square, Sharp
Stroke: Hard flood, Medium stroke
Angle: 10-15%



Stencil

2 over 2
Off Contact: 1/16" (.2cm)
Emulsion Over Mesh: 15-20%



Flash & Cure

Flash: 220°F (105°C)
Cure: 320°F (160°C)



Pigment Loading

up to 10% Wilflex PC
up to 15% Wilflex EQ
up to 30% Wilflex MX/RIO
up to 15% Rutland C3 Boosters



Additives

N/A



Storage

65-90°F (18-32°C)
Avoid direct sunlight
Use within one year of receipt



Clean Up

Dispose unused ink responsibly. Standard plastisol cleaners, press wash, or ink degreaser



Health & Safety

Find SDS information here:
www.avient.com/resources/safety-data-sheets
or contact your local CSR



AVIENT
SPECIALTY
INKS

V1.02 (Modified: 01/04/2023)

2022, Avient Corporation. Avient makes no representations, guarantees, or warranties of any kind with respect to the information contained in this document about its accuracy, suitability for particular applications, or the results obtained or obtainable using the information. Some of the information arises from laboratory work with small-scale equipment which may not provide a reliable indication of performance or properties obtained or obtainable on larger-scale equipment. Values reported as "typical" or stated without a range do not state minimum or maximum properties; consult your sales representative for property ranges and min/max specifications. Processing conditions can cause material properties to shift from the values stated in the information. Avient makes no warranties or guarantees respecting suitability of either Avient's products or the information for your process or end-use application. You have the responsibility to conduct full-scale end-product performance testing to determine suitability in your application, and you assume all risk and liability arising from your use of the information and/or use or handling of any product. AVIENT MAKES NO WARRANTIES, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE, either with respect to the information or products reflected by the information. This literature shall NOT operate as permission, recommendation, or inducement to practice any patented invention without permission of the patent owner.