



DARE TO DIY DIFFERENTLY

Liquid Rubber NeoPond Sealant is the ultimate pond coating. This well-balanced formulation is designed for UV stability, durability, elasticity, and excellent bond to most substrates. It has also been tested to be fish and plant safe.

Liquid Rubber NeoPond Sealant is so easy to apply using a brush, roller, or airless paint sprayer. Anyone can do it!



LIQUID RUBBER NEOPOND SEALANT PERFORMANCE FEATURES

- Superior Waterproofing Membrane
- Cleans Up With Soap & Water
- Ultra-Low VOC's & No Solvents
- Fish & Plant Safe
- Easy to Apply
- Water-Based



APPLICATION EQUIPMENT

Liquid Rubber NeoPond Sealant can be applied using a brush, 3/8 (10mm) roller or airless paint sprayer to provide a seamless and fully adhered membrane to most substrates. This high tensile coating is designed for multiple surfaces including wood, concrete, and metal. Apply minimum final thickness of 1 gallon per 40 sq ft (3.7 sq m). It should require around 3-4 heavy coats. Use **Liquid Rubber Geo-Textile** or **Liquid Rubber Seam Tape** to reinforce seams/joints, cracks, around penetrations etc. **Liquid Rubber Multi-Purpose Primer** is required to provide a vapor barrier and act as a bonding agent.

• Flow Rate	6 gpm
• Pressure	500-2000 PSI

• Tip Size	0.519 – 0.527
• Motor	11 HP

The sprayer must be capable of spraying an elastomeric coating.

+1 855-592-1049 | support@shopliquidrubber.com | shopliquidrubber.com

The information contained herein is the best available to Liquid Rubber Canada Inc. and its affiliated companies relating to Liquid Rubber products and the use of Liquid Rubber products. It is based on tests believed to be reliable. There is no warranty expressed or implied in association with product use. Liquid Rubber Canada Inc. assumes no liability for any damages incurred in association with the use of Liquid Rubber Canada Inc. products. Information is subject to change without notice.



DRYING TIME

At 25°C and 50% relative humidity, **Liquid Rubber NeoPond Sealant** dries to the touch in 4-6 hours and fully cures in 72 hours at 20 mils (0.5mm). Curing time increases in colder temperatures or higher humidity so environmental conditions must be considered before application. Allow 3-5 days after the last coat before filling.



SUITABLE APPLICATIONS INCLUDE BUT ARE NOT LIMITED TO

- Concrete, Wood, EPDM, Fiberglass (with the use of our EPDM Primer or Multi-Purpose Primer)
- Ask one of our technical sales representatives about other substrates



PHYSICAL PROPERTIES

Color (Liquid)	Grey to Black	Adhesion to EPDM	9 PSI
Working Temp Range	-40°C/-40°F - 80°C/176°F	Adhesion to Primed Wood	21 PSI - Cohesive Failure
Elongation	>200%	Adhesion to Primed Steel	18 PSI - Cohesive Failure
Low Temp Flex	-7°C	Adhesion to Primed Concrete	22 PSI - Cohesive Failure

LIMITATIONS & WARRANTY

- Do not apply to dirty or contaminated surfaces
- Do not apply below 10°C/50°F
- Avoid contact with solvents and solvent type adhesives
- Do not apply over coal tar
- Do not allow to freeze until fully cured

PACKAGING

- 18.9 L (5 Gal.) Pails
- 3.78 L (1 Gal.) Cans