

Clear-Seal™

100% Single-Part Urethane

TECHNICAL DATA SHEET



CSI Reference

| |
|-----------------------------|
| 03 35 00 Concrete Finishing |
| 04 2 00 Unit Masonry |
| 04 40 00 Unit Masonry |
| 05 05 13 Metal |
| 09 96 26 Finishes |
| 09 24/25 Finishes |

*Standard warranty period is 5 years

Description

Clear-Seal™ 100% Single-Part Urethane is a clear, single component, water based, VOC compliant sealer and glaze. It is a very hard urethane that offers better gloss, UV resistance, stain resistance, and is available in an anti-slip finish. The water base allows the material to penetrate and adhere to concrete, porous brick, unglazed tile and most types of decorative acrylic cement coatings.

Recommended Uses

- EIFS or cement plaster
- Primer for stucco
- Sealer for stucco
- An excellent primer for paint applications

Features & Benefits

- Surface dries in 2 to 4 hours for recoating
- Matte, satin, and high gloss
- UV Resistant
- SCAQMD VOC Compliant
- Excellent Adhesion
- Great Chemical Resistance
- Anti-Slip Finish available

Color & Finish

| Color | Finish |
|-------|--------|
| Clear | Gloss |
| | Satin |

Test Panel

Always apply Clear-Seal™ onto a mock wall or test panel. Test the wall or an actual surface area to determine acceptable color, surface porosity, application rates and

Customer Service Help-Line 888.765.7070

methods before starting general application.

In the adhesion test, apply a sample in an inconspicuous area. Allow the sample to dry and cure. Cut the film coating in a grid pattern with vertical and horizontal lines. Place tape over the grid lines and wait several minutes. Pull the tape up. If the sample is not altered after removing the tape, the surface is sufficiently prepared for application.

Coverage Rate by Substrate (theoretical)

The coverage depends on the surface. Test the product on a small area of the substrate to estimate coverage. Extremely porous surfaces may require multiple coats.

| Substrate | Sq Ft/ Gallon |
|-----------------|---------------|
| Porous Surface | 300 - 350 |
| Dense Surface | 400 |
| Painted Surface | 300 - 350 |
| Wood* | 250 |

*See application instructions for wood surfaces

The use of fluted, scored block, raked joints, sandblasted or etched surfaces will result in greater absorption and lower coverage rates, by up to 40%. Test these areas for the expected coverage rate before general application. Allow for this increased surface area when determining material requirements.

Surface Preparation

Prior to application, all surface shall be clean and dry with no oils, dirt, debris, or minerals such as efflorescence, lime and calcium. These stains, along with others, will prevent proper penetration of Clear-Seal™ 100% Single-Part Urethane to sufficiently seal for the warranty period.

The use of Rainguard's Restore-N-Prep™ Concrete and Masonry Cleaner system is recommended as a pre-treatment to clean masonry surfaces. Once clean, allow the surface to fully dry before sealing or applying a top-coat (See the Restore-N-Prep™ TDS for details).

Restore-N-Prep™ CSI Reference

| |
|----------------------------|
| 03 01 40 Concrete Finishes |
| 03 10 30 Concrete Finishes |
| 03 10 50 Concrete Finishes |
| 04 01 20 Unit Masonry |
| 04 01 40 Unit Masonry |



Application Instructions

Allow new concrete should cure at least 14 days before application of Clear-Seal™ 100% Single-Part Urethane.

Wood Application

1. Ensure the wood is clean and dry.
2. Apply your first coat of Clear-Seal™ Urethane by brushing, spraying or rolling.
3. Allow to dry for 3-4 hours.
4. Using 300 grit sandpaper, lightly sand the wood to remove any wood graining or texture.
5. Brush or blow any dust from the wood.
6. Apply 1-2 more coats over-top depending on the desired finish, allow for 1 hour to dry in-between subsequent coats.

Drying Time

Allow 3 hours before light foot traffic or recoating. Normal foot traffic may be permitted after 24 hours. Allow 48 hours prior to vehicle traffic. Allow 48 hours before placing heavy objects on the surface.

Clean Up

Uncured material can be removed with water. All empty containers must be disposed of according to local, state, and federal regulations.

Inspection

Surface must be clean, dry, and free of grease, paint, oil, dust, curing agents, or any foreign material that will prevent proper adhesion. The surface should be porous and be able to absorb water. Relative humidity in the surface should be below 80% (per ASTM F-2170). All moisture should be kept away a minimum of 48 hours before application and a min. of 48 hours after installation. This includes sprinklers, rain, fog, dew, etc.

Precautions

Use material in a well-ventilated area. Protect the work of other trades. Protect shrubbery and other plants with drop cloths. Protect automobiles and all other areas not to be coated from overspray. Remove overspray from any windows, automobiles, metal, etc. as soon as possible should it occur. To prevent permanent staining, clean spills or leaks in a timely manner.

All surfaces to be coated should be clean of any dirt and grime, efflorescence, lime run, form oils and release agents, grease, mud, excess mortar, and mold and mildew, etc. All cracks should be pointed or caulked. All voids, beeholes, masonry surface defects and openings such as conduits, pipes, drains, door frames, vents, air conditioner openings, electrical openings, control joints, or any dissimilar materials should be repaired using urethane or other approved patching. If an acid etch or an acid stain has been applied to the surface, it must be thoroughly flushed to remove all residue and then allowed to dry completely.

Do not apply to surfaces if moisture content is greater than 25% as measured with an electronic moisture meter. Do not apply materials in climates where freezing temperatures have existed prior to application. Allow adequate time for surfaces to thaw. Establish that air, surface, and material temperatures are above 40°F (4.4°C) and at least 5°F above the dew point prior to painting. Do not apply at temperatures below 40°F when temperatures are expected to drop below 40°F within 48 hours of application. Do not apply if rain, snow, or lower temperatures are expected within 48 hours. Do not apply if relative humidity is greater than 90%.

Clear water repellents are not designed to waterproof horizontal masonry surfaces such as ledges, sills, cornices and parapet walls, etc.

Store materials in a well-protected area at 45°- 90°F. Avoid freezing temperatures, direct sunlight, & moisture. Keep away from heat sources.

Safe Handling

Use product only with adequate ventilation and/or an appropriate cartridge type respirator. Avoid contact with skin and wear protective gloves. Read the Safety Data Sheet before using.



Technical Data

| | |
|--------------------|-----------------------------|
| Material Type | Water Based Urethane |
| Gloss Level | Matte 20 - 25 @ 60° |
| | Low Gloss 45 - 50 @ 60° |
| | High Gloss 75 - 80 @ 60° |
| Flash Point | Non-Flammable |
| V.O.C. | <50 g/L V.O.C. Compliant |
| Weight | Approximately 8.5 lbs./Gal. |
| Color of Material | Clear to Slightly Cloudy |
| Odor | Slight Latex Smell |
| pH Value | Approximately 7.5 |
| Viscosity | 9.6 Seconds No. 4 Ford Cup |
| Surface Dry/Recoat | 2 - 4 Hours |
| Volume Solids | 50% |

Warranties

Rainguard Brands, LLC guarantees that this product is free from manufacturing defects and complies with our published specifications. In the event that the buyer proves that the goods received do not conform to these specifications or were defectively manufactured, the buyer's remedies shall be limited to either the return of the goods and repayment of the purchase price or replacement of the defective material at the option of the seller. Rainguard Brands, LLC makes no other warranty, expressed or implied, and all warranties of merchantability and fitness for a particular purpose are hereby disclaimed. Manufacturer or seller shall not be liable for prospective profits or consequential damages resulting from the use of this product. Manufacturer shall not be liable for material used outside of its shelf life. For product dating, please refer to the batch number on the product or contact Rainguard Brands, LLC.

Surface conditions and application variables are out of the control of Rainguard Brands, LLC. As such, the applicator agrees to: Follow recommended application instructions, acknowledge limitations outlined in this technical data sheet, contact the manufacturer in the event there are any uncertainties, perform a test panel to confirm fit and finish before any general application. The data on this sheet represent typical values. Since application variables are a major factor in product performance, this information should serve only as a general guide. Rainguard Brands assumes no obligation or liability for use of this information. Contact manufacturer at 888-765-7070 before bidding to confirm warranty provisions and procedures.

SELLER'S LIABILITY UNDER THE SALE OF THIS PRODUCT IS LIMITED TO REPLACING DEFECTIVE PRODUCT. HOWEVER, IF SELLERS FAILS IN ITS ATTEMPT TO REPLACE THE DEFECTIVE PRODUCT, BUYER WILL BE ENTITLED TO A REFUND OF MONIES PAID TO SELLER UNDER THIS PRODUCT WARRANTY. SELLER IS NOT LIABLE FOR BUYER'S LOSS OF PROFITS, BUSINESS GOODWILL, OR OTHER CONSEQUENTIAL DAMAGES, DESPITE ANY FAILURE TO REPLACE THE PRODUCT. BUYER HAS ACCEPTED THIS RESTRICTION ON ITS RIGHT TO RECOVER CONSEQUENTIAL DAMAGES AS PART OF ITS BARGAIN WITH SELLER. BUYER REALIZES AND ACKNOWLEDGES THAT THE PRICE OF THE PRODUCT WOULD BE HIGHER IF SELLER WERE REQUIRED TO BE RESPONSIBLE FOR BUYER'S CONSEQUENTIAL DAMAGES."

© 2023 RAINGUARD BRANDS, LLC. All rights reserved.

[END]