

METALIQ PATINE

TECHNICAL DATA SHEET

UPDATE: 18.02.2022

BRAND PRIMACOL® DECORATIVE

PRODUCT Metaliq Patine

Surface patination paint

Steel wall efet



1-2 h

PACK 0,5 kg

PROPERTIES Decorative paste in ready-to-use colour to create a patinated effect on the surface. It is

applied between Metaliq Paste and Metaliq Top.

SUBSTRATE The substrate to be decorated with Metaliq Patine should be prepared with Decobase paint

PREPARATION and Metaliq Paste as described in Metaliq Paste.

APPLICATION Mix the product thoroughly. Apply it with a Venetian trowel to the dry Metaliq Paste surface.

Apply a small amount selectively and in a thin layer. After 12 hours, wipe the surface with fine sandpaper and dedust it. Shine the effect with a clean spatula. Apply Metaliq Top in a

selected color.

Always test the product on the main surface before use. The effect obtained depends on

many factors, such as the preparation of the substrate, the tools used, the application

technique.

STORAGE Store the product in a tightly closed original container at 5 - 30°C and out of the reach of

children. Do not expose it to sunlight. Protect from freezing.

SAFETY Product treated with biocidal product. Contains C(M) IT /MIT (3:1). Contains a reaction mass

of 5-chloro-2-methyl-2H-isothiazol-3-one and 2-methyl-2H-isothiazol-3-one (3:1) and 1,2-

benzisothiazol-3(2H)-one. May produce an allergic reaction.

TECHNICAL DATA

Color

Chemical composition Water, polymer solution, fillers, additives Tools Steel float

Green Touch dry

Odour Mild, charakteristic Completely dry 24 h

Coverage per 1/ 10mi

Density 1,70 kg/dm³ Coverage per +/- 10m²

Finish Matte/ semi-matte/ gloss (depending on the application Diluent Water

(depending on the application Diluent Wate technique)

Number of layers 1 Tool cleaning Water with detergent



METALIQ PATINE

TECHNICAL DATA SHEET

UPDATE: 18.02.2022

VOC limit

(cat. A/I/FW): 200 g/l, the product contains max. 200 g/l.

LEGAL INFORMATION

The information contained in this technical data sheet provides recommendations and possible examples. The information provided reflects the current state of our knowledge and experience and does not free the user from the obligation to make his or her own tests to check the suitability of the product for the intended purpose. The manufacturer reserves the right to change this technical information without informing the client.