



Technical Data Sheet

Description:

This synthetic rubber offers exceptionally good resistance to weather, ozone, sunlight and oxidation. Hypalon has excellent properties for alkalis and acids. This sheet is not recommended for aldehydes, aromatic or chlorinated solvents. Hypalon rubber sheet is recommended for extended outdoor applications.

Physical Properties	
Hardness (60 Shore A)	+/- 5
Tensile Strength (psi)	1100
Elongation at Break (%)	300
Temperature Range (°F)	-22 to 248
Temperature Range (°C)	-30 to 120



Toronto • Montreal
www.specialtygaskets.com

DISCLAIMER: The information in this Technical Data Sheet is believed to be correct as of the date issued. Specialty Gaskets Inc. MAKES NO WARRANTIES, EXPRESSED OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, ANY IMPLIED WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE OR COURSE OF PERFORMANCE OR USAGE OF TRADE. User is responsible for determining whether the Specialty Gaskets Inc. product is fit for a particular purpose and suitable for user's method of use or application. Given the variety of factors that can affect the use and application of a Specialty Gaskets Inc. Product it is essential that the user evaluate the Specialty Gaskets Inc. product to determine whether it is fit for a particular purpose and suitable for user's method of use or application.



ISO 9001