

## Castrol Brayco 1720 Series

Perfluoroether Lubricant Gear, Pump and Lubricating Oil, Chemically Inert, Oxidizer Compatible

### Description

Castrol Brayco® 1720 Series Oils are clear, colorless low molecular weight perfluoroether oils. The oils are chemically inert to virtually all chemicals, and safe to use in direct contact with oxidants such as LOX/GOX and chlorine. Castrol Brayco® 1720 Series Oils are nonflammable and non-toxic. Castrol Fluoroclean™ X100 and Castrol Fluoroclean™ HE can be used to remove these lubricants. Refer to the data sheets for information regarding these products.

### Application

Castrol Brayco® 1720 Series Oils are intended for use as gear, pump, and lubricating oils where direct or indirect contact with aggressive chemicals, oxidants, and low temperatures are routine. The Castrol Brayco® 1720 Series Oils can also be used as vacuum pump oils in operations requiring vapor pressures as low as 10<sup>-4</sup> torr. Perfluorinated fluids, in general, exhibit excellent shelf lives due to their intrinsic inertness.

### Typical Characteristics

Test (ASTM)	Description	CASTROL BRAYCO®			
		1721	1722	1723	1724
D 287	Specific Gravity @ 16/16°C (60/60°F) Pounds per Gallon @ 16°C/60°F	1.848 15.4	1.885 15.7	1.887 15.72	1.907 15.89
D 445	Kinematic Viscosity, cSt @ 100°C (212°F) @ 40°C (104°F) @ 20°C (68°F) @ 0°C (32°F) @ -20°C (-4°F) @ -40°C (-40°F) @ -54°C (-65°F)	1.43 5.1 10.3 22 90 2500 60,000	4.04 21.8 56.4 240 1600 18,000 250,000	5.19 30.1 79.1 310 2100 30,000 ND	9.46 67.7 198.1 800 7000 ND ND
D 2270	Viscosity Index	ND	60	101	114
D 97	Pour Point, °C (°F)	-69 (-90)	-57 (-70)	-48 (-55)	-42 (-45)
D 972	Evaporation Loss, % wt 22 hrs @ 60°C (140°F) 22 hrs @ 120°C (248°F)	6.33 ---	1.39 18	1.6 26.2	0.7 9.3
D 2266	Four-Ball Wear-Test, AWSD, mm 600 rpm, 2 hrs, 75°C (167°F), 40 kgf	0.59	0.55	0.52	0.42
D 2783	Four-Ball EP Weld Point Weld Point, kgf Load Wear Index	250 50	250 75	315 85	315 115
Knudsen	Vapor Pressure, torr 20°C (68°F) 100°C (212°F)	1 x 10 <sup>-1</sup> 1 x 10 <sup>-1</sup>	1 x 10 <sup>-3</sup> 1 x 10 <sup>-1</sup>	1 x 10 <sup>-4</sup> 1 x 10 <sup>-1</sup>	1 x 10 <sup>-4</sup> 1 x 10 <sup>-1</sup>
D 1331	Surface Tension 20°C (68°F), dynes/cm	19	21	21	21

## Additional Information

### Temperature Range

Castrol Brayco®1721 -54°C to 93°C (-65°F to 200°F)  
Castrol Brayco®1722 -34°C to 149°C (-30°F to 300°F)  
Castrol Brayco®1723 -34°C to 163°C (-30°F to 325°F)  
Castrol Brayco®1724 -29°C to 177°C (-20°F to 350°F)

### Limitations

Castrol Brayco® 1720 Series Oils are compatible with all commonly utilized materials, plastics, and elastomers. Castrol Brayco® 1720 Series Oils may be adversely affected by Lewis Acid Catalysts such as AlCl<sub>3</sub>, at elevated temperatures. Newly exposed rubbing surfaces of aluminum, magnesium and titanium may react with Castrol Brayco®1720 Series Oils under certain conditions. Such systems should be thoroughly evaluated. Surfaces must be well cleaned of organic rust inhibitors prior to oil application to insure proper lubrication.

### Packaging

Castrol Brayco®1720 Series Oils are available in 4 pound (1 quart), 16 pound (1 gallon) bottles and 75 pound pails.

Castrol, Brayco, and the Castrol logo are trademarks of Castrol Limited, used under license

This data sheet and the information it contains is believed to be accurate as of the date of printing. However, no warranty or representation, express or implied, is made as to its accuracy or completeness. Data provided is based on standard tests under laboratory conditions and is given as a guide only. Users are advised to ensure that they refer to the latest version of this data sheet.

It is the responsibility of the user to evaluate and use products safely, to assess suitability for the intended application and to comply with all applicable laws and regulations. Material Safety Data Sheets are available for all our products and should be consulted for appropriate information regarding storage, safe handling, and disposal of the product. No responsibility is taken by either BP plc or its subsidiaries for any damage or injury resulting from abnormal use of the material, from any failure to adhere to recommendations, or from hazards inherent in the nature of the material. All products, services and information supplied are provided under our standard conditions of sale. You should consult our local representative if you require any further information.

Castrol Industrial North America Inc. 150 West Warrenville Road, 605 3E Naperville, IL 60563  
Tel: (877) 641 1600 Fax: (877) 648 9801  
[www.castrol.com/industrial](http://www.castrol.com/industrial)